

09/762044

TRANSMITTAL LETTER TO THE UNITED STATES

ATTORNEY'S DOCKET NUMBER 49248

DESIGNATED/ELECTED OFFICE (DO/EO/US)
CONCERNING A FILING UNDER 35 U.S.C. 371

U.S. APPLICATION NO. (If known, see 37 CFR 1.5)

INTERNATIONAL APPLICATION NO.	INTERNATIONAL FILING DATE	PRIORITY DATE CLAIMED
PCT/EP 99/05407	28 July 1999	4 August 1998 13 October 1998

TITLE OF INVENTION: SOIL-APPLIED GRANULES WITH CONTROLLED RELEASE OF ACTIVE INGREDIENT(S)
(SOIL-APPLIED CR GRANULES)APPLICANT(S) FOR DO/EO/US Reinhold STADLER, Reiner KOBER, Karl-Heinrich SCHNIEDER, Reinhold SAUR,
Herbert BAYER, Karl KOLTER, Michael SEUFERT

Applicant herewith submits to the United States Designated/Elected Office (DO/EO/US) the following items and other information:

1. /X/ This is a FIRST submission of items concerning a filing under 35 U.S.C. 371.
2. / / This is a SECOND or SUBSEQUENT submission of items concerning a filing under 35 U.S.C. 371.
3. /X/ This express request to begin national examination procedures (35 U.S.C. 371(f)) at any time rather than delay examination until the expiration of the applicable time limit set in 35 U.S.C. 371(b) and PCT Articles 22 and 39(1).
4. /X/ A proper Demand for International Preliminary Examination was made by the 19th month from the earliest claimed priority date.
5. /X/ A copy of the International Application as filed (35 U.S.C. 371(c)(2)).
- a. /X/ is transmitted herewith (required only if not transmitted by the International Bureau).
b. / / has been transmitted by the International Bureau.
c. / / is not required, as the application was filed in the United States Receiving Office (RO/USO).
6. /X/ A translation of the International Application into English (35 U.S.C. 371(c)(2)).
7. / / Amendments to the claims of the International Application under PCT Article 19 (35 U.S.C. 371(c)(3)).
- a. / / are transmitted herewith (required only if not transmitted by the International Bureau).
b. / / have been transmitted by the International Bureau.
c. / / have not been made; however, the time limit for making such amendments has NOT expired.
d. / / have not been made and will not be made.
8. / / A translation of the amendments to the claims under PCT Article 19 (35 U.S.C. 371(c)(3)).
9. /X / An oath or declaration of the inventor(s) (35 U.S.C. 171(c)(4)).
10. / / A translation of the annexes to the International Preliminary Examination Report under PCT Article 36 (35 U.S.C. 371(c)(5)).
- Items 11. to 16. below concern other document(s) or information included:
11. /X / An Information Disclosure Statement under 37 CFR 1.97 and 1.98.
12. /X / An assignment document for recording. A separate cover sheet in compliance with 37 CFR 3.28 and 3.31 is included.
13. /X / A FIRST preliminary amendment.
/ / A SECOND or SUBSEQUENT preliminary amendment.
14. / / A substitute specification.
15. / / A change of power of attorney and/or address letter.
16. /X / Other items or information.
International Search Report
International Preliminary Examination Report



101020 4402250

U.S. Appl. No. (if Known) INTERNATIONAL APPL. NO.

ATTORNEYS DOCKET NO.

09/762044 PCT/JP99/05407

49248

17. (X) The following case or cases submitted

CALCULATIONSPTO USE ONLY

BASIC NATIONAL FEE (37 CFR 1.492(a)(1)-(5)):

Search Report has been prepared by the

EPO or JPO.....\$860.00

860.00

International preliminary examination fee paid to USPTO

(37 CFR 1.482).....\$750.00

No international preliminary examination fee paid to

USPTO (37 CFR 1.482) but international search fee paid

to USPTO (37 CFR 1.445(a)(2)).....\$700.00

Neither international preliminary examination fee

(37 CFR 1.482) nor international search fee

(37 CFR 1.445(a)(2)) paid to USPTO\$ 970.00

International preliminary examination fee paid to

USPTO (37 CFR 1.482) and all claims satisfied pro

visions of PCT Article 33(2)-(4).....\$96.00

ENTER APPROPRIATE BASIC FEE AMOUNT = \$ 860.00

Surcharge of \$130.00 for furnishing the oath or declaration

later than 1/20 / 30 months from the earliest

claimed priority date (37 CFR 1.492(e)).

Claims	Number Filed	Number Extra	Rate
Total Claims	11	-20	X\$18.
Indep. Claims	1	-3	X\$80.
Multiple dependent claim(s) (if applicable)		+270.	
TOTAL OF ABOVE CALCULATION			= 860.00

Reduction of 1/2 for filing by small entity, if applicable.

Verified Small Entity statement must also be filed

(Note 37 CFR 1.9, 1.27, 1.28).

SUBTOTAL = 860.00

Processing fee of \$130. for furnishing the English

translation later than 1/20 / 30 months from the

earliest claimed priority date (37 CFR 1.492(f)).

TOTAL NATIONAL FEE = 860.00

Fee for recording the enclosed assignment (37 CFR 1.21(h)).

The assignment must be accompanied by an appropriate cover

sheet (37 CFR 3.28, 3.31) \$40.00 per property = 40.00

TOTAL FEES ENCLOSED = \$ 900.00

Amount to be

refunded: \$

Charged \$

a./X/ A check in the amount of \$ 900. to cover the above fees is enclosed.

b./I Please charge my Deposit Account No. _____ in the amount of \$ _____ to cover the above fees. A duplicate copy of this sheet is enclosed.

c./X/ The Commissioner is hereby authorized to charge any additional fees which may be required, or credit any overpayment to Deposit Account No. **11-0345**. A duplicate copy of this sheet is enclosed.**NOTE:** Where an appropriate time limit under 37 CFR 1.494 or 1.495 has not been met, a petition to revive (37 CFR 1.137(a) or (b) must be filed and granted to restore the application to pending status.**SEND ALL CORRESPONDENCE TO:**KEIL & WEINKAUF
1101 Connecticut Ave., N.W.
Washington, D. C. 20036

SIGNATURE

Herbert B. Keil

NAME

Registration No. 18,967

09/762044-020101

1. Soil-applied CR granules obtainable by applying an active-ingredient-comprising coating to a solid carrier in a fluidized bed with a defined heat input adjustable to 6000 to 25,000 KJ/KG [sic] of coating polymer.
3. Soil-applied CR granules as claimed in claim 2 comprising, as coating polymer, a dispersion from amongst the following groups: butyl acrylate/styrene copolymers, copolymer dispersions of acrylic and methacrylic esters, polyethylene wax emulsions, polyesters composed of the following units: 50 mol% dimethyl terephthalate + approx. 50 mol% adipic acid + 150 mol% 1,4-butanediol + trace elements, mixture of 10-95% polyvinyl acetate + 5-90% N-vinylpyrrolidone-comprising [sic] polymers, ethylene/methacrylic acid zinc salt.
6. Soil-applied CR granules as claimed in claim 1 [any one of claims 1-5], comprising an active ingredient from the group of the systemically acting strobilurins, the azoles or the salicylates.
7. Soil-applied CR granules as claimed in claim 1 [any of claims 1-5], comprising, as active ingredient, 5-methyl [sic]benzo[1,2,3]thiadiazole-7-carbothioate.

9. A process for the preparation of Soil-applied CR granules as claimed in claim 1, [any one of claims 1-8] which comprises applying, to a carrier, first the active ingredient and then the coating comprising at least one coating polymer and, if appropriate additives in a fluidized bed, micropores being generated in the coating by abrasion or by the directed addition of water-soluble additives (lime, starch).

10. A method for controlling phytopathogenic fungi, undesired vegetation, undesired attack by insects and/or for regulating the growth of plants, which comprises allowing Soil-applied CR granules as claimed in claim 1 [any one of claims 1 to 9] to act on plants, their environment or on seed.

Cancel claim 11.

REMARKS

The claims have been amended to eliminate multiple dependency and to put them in better form for U.S. filing. No new matter is included. A clean copy of the claims is attached. Favorable action is solicited.

Respectfully submitted,

KEIL & WEINKAUF


Herbert B. Keil
Reg. No. 18,967

1101 Connecticut Ave., N.W.
Washington, D.C. 20036

(202)659-0100


10020-44029260

CLEAN COPY OF CLAIMS AS FILED - OZ 49248

1. Soil-applied CR granules obtainable by applying an active-ingredient-comprising coating to a solid carrier in a fluidized bed with a defined heat input adjustable to 6000 to 25,000 KJ/KG of coating polymer.
2. Soil-applied CR granules as claimed in claim 1 with an active-ingredient-comprising coating of
 - 0.1–25% by weight of one or more active ingredients
 - 1–40% by weight of one or more coating polymers
 - 0–60% by weight of one or more additives,the total of the % by weight of the compounds in the coating being 100% by weight.
3. Soil-applied CR granules as claimed in claim 2 comprising, as coating polymer, a dispersion from amongst the following groups: butyl acrylate/styrene copolymers, copolymer dispersions of acrylic and methacrylic esters, polyethylene wax emulsions, polyesters composed of the following units: 50 mol% dimethyl terephthalate + approx. 50 mol% adipic acid + 150 mol% 1,4–butanediol + trace elements, mixture of 10-95% polyvinyl acetate + 5–90% N–vinylpyrrolidone–comprising polymers, ethylene/methacrylic acid zinc salt.
4. Soil-applied CR granules as claimed in claim 3 comprising, as coating polymer, at least one from amongst the group of the biodegradable polyesters.

03162044-03010

5. Soil-applied CR granules as claimed in claim 1 comprising, as active ingredient, at least one fungicidal compound of the formula I from amongst the class of the strobilurins.



in which the substituents have the following meanings:

A is NOCH_3 , CHOCH_3 , CHCH_3 ;

Y is O, NH;

T is oxygen or oxymethylene;

Z is a group X, $\text{N}=\text{C}(\text{R}^1)\text{W}$ or $\text{N}=\text{C}(\text{R}^1)-\text{C}(\text{R}^2)=\text{NOR}^3$;

X is unsubstituted or substituted heterocyclyl, unsubstituted or substituted aryl, unsubstituted or substituted hetaryl;

W is unsubstituted or substituted alkyl, unsubstituted or substituted alkenyl, unsubstituted or substituted alkynyl, unsubstituted or substituted cycloalkyl,

unsubstituted or substituted cycloalkenyl, unsubstituted or substituted heterocyclyl, unsubstituted or substituted aryl or unsubstituted or substituted hetaryl;

R¹ is hydrogen, cyano, C₁-C₄-alkyl, C₁-C₄-haloalkyl, C₁-C₄-alkoxy, C₁-C₄-alkoxy-C₁-C₄-alkyl, C₃-C₆-cycloalkyl;

R² is hydrogen, cyano, halogen, C(R^d)=NOR³ or W, OW, SW or NR^eW, where

R^e is hydrogen, alkyl, alkenyl or alkynyl;

R^d is hydrogen or alkyl;

R³ is hydrogen, unsubstituted or substituted alkyl, unsubstituted or substituted alkenyl or unsubstituted or substituted alkynyl,

or a salt thereof.

6. Soil-applied CR granules as claimed in claim 1, comprising an active ingredient from the group of the systemically acting strobilurins, the azoles or the salicylates.
7. Soil-applied CR granules as claimed in claim 1, comprising, as active ingredient, S-methyl benzo[1,2,3]thiadiazole-7-carbothioate.
8. Soil-applied CR granules as claimed in claim 1, comprising, as carrier, water-soluble, water-insoluble or biodegradable granules.
9. A process for the preparation of Soil-applied CR granules as claimed in claim 1, which comprises applying, to a carrier, first the active ingredient and then the coating comprising at least one coating polymer and, if appropriate additives in a fluidized bed, micropores being generated in the coating by abrasion or by the

CLEAN CLAIMS OZ 49248

directed addition of water-soluble additives (lime, starch).

10. A method for controlling phytopathogenic fungi, undesired vegetation, undesired attack by insects and/or for regulating the growth of plants, which comprises allowing Soil-applied CR granules as claimed in claim 1 to act on plants, their environment or on seed.

09752044-020104

Soil-applied granules with controlled release of active ingredient(s) (soil-applied CR granules)

- 5 The present invention relates to soil-applied CR granules which can be obtained by applying an active-ingredient-comprising coating to a solid carrier in a fluidized bed with a defined heat input adjustable to 6000 to 25,000 KJ/Kg [sic] of coating polymer, to soil-applied CR granules with an active-ingredient-
- 10 comprising coating of 0.1-25% by weight of one or more active ingredients, 1-40% by weight of one or more coating polymers and 0-60% by weight of one or more additives, to a process for the preparation of these soil-applied granules, and to a method for controlling phytopathogenic fungi, undesired vegetation,
- 15 undesired attack by insects and/or for regulating the growth of plants using the soil-applied CR granules according to the invention.

- It is generally known to use coating polymers for fixing crop
- 20 protection active ingredients on a solid carrier in such a manner that the active ingredient is only gradually released and can thus develop its action over a prolonged period ("slow-release formulation"). WO-A 92 17424 describes fertilizer granules which are coated with an ionically and covalently crosslinked copolymer
- 25 of ethylene and the zinc salt of methacrylic acid. EP-A 0 380 836 discloses the non-covalently crosslinked, partially neutralized equivalents to the copolymers described in WO-A-9217424 as suitable for coating agrochemicals which are to be released slowly and in a controlled fashion. A process for coating small
- 30 particles which comprise an active ingredient, which may be a crop protection agent, is described in US-A 4,756,844. However, the disadvantage of the current products is that they still tend to agglomerate greatly, which means that the flowability of the formulated product is lost and that the release rate of the
- 35 active ingredient cannot be adjusted by means of process control.

It is an object of the present invention to find a formulation for crop protection active ingredients which does not exhibit these disadvantageous characteristics.

40

It is a further object of the present invention to develop slow-release formulations which allow the use of phytotoxic active ingredients for treating plant diseases.

- 45 It is a further object of the present invention to develop novel coating techniques using specific and novel coating polymers which provide the encapsulated active ingredient in a tailored

09762044, 020101

manner, with a controlled release rate, systemically and transapically over a substantial vegetation period of the plant in the form of granules for co-drilling.

5 We have found that this object is achieved by soil-applied CR granules as claimed in claim 1.

There has furthermore been found a process for their preparation and the use of those compositions which comprise fungicidal crop
10 protection active ingredient for controlling harmful fungi.

The construction of semipermeable monolayer or polylayer coatings on the soil-applied CR granules and exact metering of the heat input supplied into a fluidized-bed apparatus allows the active
15 ingredient to be available for up to a period of over 9 months.

Preferred soil-applied CR granules according to the invention are intended to offer complete protection against fungal pathogens, to be nonphytotoxic and, finally, to replace fungicide spray
20 treatments when they are applied by co-drilling together with the seed of the annual or perennial plant.

Suitable crop protection active ingredients are herbicidal, growth-regulatory, insecticidal and, in particular, fungicidal
25 active ingredients.

Suitable systemic active ingredients which are available belong to the fungicidal substance classes of the azoles, morpholines, valinamides, strobilurins and salicylates as distant derivatives
30 of active ingredients of the Bion® type. Surprisingly, selected experiments in which application was effected in the form of the soil-applied CR granules according to the invention led to similarly successful biological results as when two spray treatments with commercially available fungicides were carried
35 out; in some cases, the biological results were even better.

Thus, surprisingly, when using acetylsalicylic acid as active ingredient component, activity-enhancing effects were observed upon soil application and combination with strobilurins.
40

The following list of herbicides identifies examples of active ingredients which are possible:

- b1 1,3,4-Thiadiazoles:
buthidazole, cyprazole
- b2 Amides:
5 allidochlor (CDAA), benzoylprop-ethyl, bromobutide,
chlorthiamid, dimepiperate, dimethenamid, s-dimethenamid,
diphenamid, etobenzanid (benzchlomet), flamprop-methyl,
fluthiamide, fosamin, isoxaben, monalide, naptalame, pronamid
(propyzamid), propanil
- 10 b3 Aminophosphoric acids:
bilanafos, (bialaphos), buminafos, glufosinate-ammonium,
glyphosate, sulfosate
- 15 b4 Aminotriazoles:
amitrol
- b5 Anilides:
anilofos, mefenacet
- 20 b6 Aryloxyalkanoic acids:
2,4-D, 2,4-DB, clomeprop, dichlorprop, dichlorprop-P,
dichlorprop-P (2,4-DP-P), fenoprop (2,4,5-TP), fluoroxypyr,
MCPA, MCPB, mecoprop, mecoprop-P, napropamide, napropanilide,
25 triclopyr
- b7 Benzoic acids:
chloramben, dicamba
- 30 b8 Benzothiadiazinones:
bentazone
- b9 Bleachers:
clomazone (dimethazone), diflufenican, fluorochloridone,
35 flupoxam, fluridone, pyrazolate, sulcotrione (chlormesulone),
isoxaflutole, isoxachlortole, mesotrione
- b10 Carbamates:
asulam, barban, butylate, carbetamid, chlorbufam,
40 chlorpropham, cycloate, desmedipham, di-allate, EPTC,
esprocarb, molinate, orbencarb, pebulate, phenisopham,
phenmedipham, propham, prosulfocarb, pyributicarb,
sulf-allate (CDEC), terbucarb, thiobencarb (benthicarb),
tiocarbazil, tri-allate, vernolate
- 45 b11 Quinoline [sic] acids:

quinclorac, quinmerac

- b12 Chloracetanilides:
5 acetochlor, alachlor, butachlor, butenachlor, diethatyl [sic] ethyl, dimethachlor, metazachlor, metolachlor, pretilachlor, propachlor, prynachlor, terbuchlor, thenylchlor, xylachlor, s-metolachlor
- b13 Cyclohexenones:
10 alloxydim, tepraloxydim, clethodim, cloproxydim, cycloxydim, sethoxydim, tralkoxydim,
2-{1-[2-(4-chlorophenoxy)propyloxyimino]butyl}-3-hydroxy-5-(2H-tetrahydrothiopyran-3-yl)-2-cyclohexen-1-one, butroxydim, clefoxydim
- 15 b14 Dichloropropionic acids:
dalapon
- b15 Dihydrobenzofurans:
20 ethofumesate
- b16 Dihydrofuran-3-ones:
flurtamone
- 25 b17 Dinitroanilines:
benefin, butralin, dinitramin, ethalfluralin, fluchloralin, isopropalin, nitralin, oryzalin, pendimethalin, prodiamine, profluralin, trifluralin
- 30 b18 Dinitrophenols:
bromofenoxim, dinoseb, dinoseb-acetate, dinoterb, DNOC
- b19 Diphenyl ethers:
35 acifluorfen-sodium, aclonifen, bifenox, chlornitrofen (CNP), difenoxuron, ethoxyfen, fluorodifen, fluoroglycofen-ethyl, fomesafen, furyloxyfen, lactofen, nitrofen, nitrofluorfen, oxyfluorfen
- b20 Dipyridylenes:
40 cyperquat, difenzoquat-methylsulfate, diquat, paraquat dichloride
- b21 Ureas:
45 benzthiazuron, buturon, chlorbromuron, chloroxuron, chlortoluron, cumyluron, dibenzyluron, cycluron, dimefuron, diuron, dymron, ethidimuron, fenuron, fluormeturon, isoproturon, isouron, karbutilat, linuron,

methabenzthiazuron, metobenzuron, metoxuron, monolinuron,
monuron, neburon, siduron, tebuthiuron, trimeturon

- b22 Imidazoles:
5 isocarbamid
- b23 Imidazolinones:
imazamethapyr, imazapyr, imazaquin, imazethabenz-methyl
(imazame), imazethapyr, imazapic
- 10 b24 Oxadiazoles:
methazole, oxadiargyl, oxadiazon
- b25 Oxiranes:
15 tridiphan
- b26 Phenols:
bromoxynil, ioxynil
- 20 b27 Phenoxyphenoxypropionic esters:
clodinafop, cloquintocet, cyhalofop-butyl, diclofop-methyl,
fenoxaprop-ethyl, fenoxaprop-p-ethyl, fenthiaapropethyl,
fluazifop-butyl, fluazifop-p-butyl, haloxyfop-ethoxyethyl,
haloxyfop-methyl, haloxyfop-p-methyl, isoxapyrifop,
25 propaquizafop, quizalofop-ethyl, quizalofop-p-ethyl,
quizalofop-tefuryl
- b28 Phenylacetic acids:
chlorfenac (fenac)
- 30 b29 Phenylpropionic acids:
chlorophenprop-methyl [sic]
- b30 Protoporphyrinogen IX oxydase inhibitors:
35 benzoefenap, cinidon-ethyl, flumiclorac-pentyl, flumioxazin,
flumipropyn, flupropacil, fluthiacet-methyl, pyrazoxyfen,
sulfentrazone, thidiazimin, carfentrazone
- b31 Pyrazoles
40 nipyraclufen, pyraflufen-ethyl
- b32 Pyridazines:
chloridazon, maleic hydrazide, norflurazon, pyridate
- 45 b33 Pyridinecarboxylic acids:
clopalyrid, dithiopyr, picloram, thiazopyr, diflufenzopyr

09762044:020104

- b34 Pyrimidyl ethers:
pyrithiobac-acid, pyrithiobac-sodium, KIH-2023, KIH-6127,
pyribenzoxym
- 5 b35 Sulfonamides:
flumetsulam, metosulam
- b36 Sulfonylureas:
amidosulfuron, azimsulfuron, bensulfuron-methyl,
10 chlorimuron-ethyl, chlorsulfuron, cinosulfuron,
cyclosulfamuron, ethametsulfuron methyl, ethoxysulfuron,
flazasulfuron, halosulfuron-methyl, imazosulfuron,
metsulfuron-methyl, nicosulfuron, primisulfuron, prosulfuron,
pyrazosulfuron-ethyl, rimsulfuron, sulfometuron-methyl,
15 thifensulfuron-methyl, triasulfuron, tribenuron-methyl,
triflusalufuron-methyl,
N-[[[4-methoxy-6-(trifluoromethyl)-1,3,5-triazin-2-yl]amino]-
carbonyl]-2-(trifluoromethyl)benzenesulfonamide,
sulfosulfuron, idosulfuron
- 20 b37 Triazines:
ametryn, atrazine, aziprotryn, cyanazine, cyprazine,
desmetryn, dimethamethryn, dipropetryn, eglinazine-ethyl,
hexazinone, procyzazine, prometon, prometryn, propazine,
25 secbumeton, simazine, simetryn, terbumeton, terbutryn,
terbutylazine [sic], trietazine
- b38 Triazinones:
ethiozin, metamitron, metribuzin
- 30 b39 Triazolecarboxamides:
triazofenamid
- b40 Uracils:
35 bromacil, lenacil, terbacil
- b41 Various:
benazolin, benfuresate, bensulide, benzofluor, butamifos,
cafenstrole, chlorthal-dimethyl (DCPA), cinmethylin,
40 dichlobenil, endothall, fluorbentranil, mefluidide,
perfluidone, piperophos, flucabazone, oxaciclomefone (MY 100)

The following list of compounds with growth-regulatory activity
shows examples of active ingredients which are possible from
45 amongst this group:

- 1-naphthylacetamide, 1-naphthylacetic acid, 2-naphthylloxyacetic acid, 3-CPA, 4-CPA, ancymidol, anthraquinone, BAP, butifos; tribufos, butralin, chlorflurenol, chlormequat, clofencet, cyclanilide, daminozide, dicamba, dikegulac-sodium, dimethipin,
- 5 chlorfenethol, etacelasil, ethephon, ethychlozate, fenoprop, 2,4,5-TP, fluoridamid, flurprimidol, flutriafol, gibberellic acid, gibberillin, guazatine, imazalil, indolylbutyric acid, indolylacetic acid, karetazan, kinetin, lactidichlor-ethyl, maleic hydrazide, mefluidide, mepiquat-chloride, naptalam,
- 10 paclobutrazole, prohexadione calcium, quinmerac, sintofen, tetcyclacis, thidiazuron, triiodobezoic [sic] acid, triapenthenol, triazethan, tribufos, trinexapacethyl, uniconazole.
- 15 The list of insecticides which follows indicates examples of active ingredients which are possible:
- Neonicotinoids/chloronicotinyl compounds:
- 20 imidacloprid, acetamiprid, nitenpyram, thiacloprid, thiamethoxam, tefuranitidine, organophosphates,
- acephate, azinphos-methyl, chlorpyrifos, dimethoate, disulfoton, fosthiazate, methamidophos, methidathion, methyl-parathion,
- 25 oxydemeton-methyl, phorate, phosalone,
- phosmet, profenofos, trichlorfon
- carbamates such as
- 30 alanycarb, aldicarb, benfuracarb, carbofuran, carbosulfan, furathiocarb, methomyl, oxamyl, pirimicarb, thiodicarb
- pyrethroids such as
- 35 bifenthrin, cyfluthrin, cypermethrin, deltamethrin, esfenvalerate,
- fenpropathrin, lambda-cyhalothrin, permethrin, tau-fluvalinate,
- 40 tralomethrin, zeta-cypermethrin
- urea derivatives such as
- diflubenzuron, flucyclohexuron, flufenoxuron, hexaflumuron,
- 45 lufenuron,

0050/49248

novaluron, triflumuron

juvenoids such as

- 5 buprofezin, diofenolan, fenoxycarb, pyriproxifen, methoxyfenozide, tebufenozide

various such as

- 10 abamectin, spinosad, amitraz, cartap, chlorfenapyr, diafenthiuron, fipronil

pyridaben, tebufenpyrad, fenazaquin, fenpyroximate, thiocyclam, silafluofen

15

The list of fungicides which follows shows examples of active ingredients which are possible:

sulfur, dithiocarbamates and their derivatives, such as iron(III)

- 20 dimethyldithiocarbamate, zinc dimethyldithiocarbamate, zinc ethylenebisdithiocarbamate, manganese ethylenebisdithiocarbamate, manganese zinc ethylenediaminebisdithiocarbamate, tetramethylthiuram disulfides [sic], ammonia complex of zinc (N,N-ethylenebisdithiocarbamate), ammonia complex of zinc 25 (N,N'-propylenebisdithiocarbamate), zinc (N,N'-propylenebisdithiocarbamate), N,N'-polypropylenebis(thiocarbamoyl)disulfide;

nitro derivatives, such as dinitro(1-methylheptyl)phenyl

- 30 crotonate, 2-sec-butyl-4,6-dinitrophenyl 3,3-dimethylacrylate, 2-sec-butyl-4,6-dinitrophenyl isopropyl carbonate, diisopropyl 5-nitroisophthalate;

heterocyclic substances, such as 2-heptadecyl-2-imidazoline

- 35 acetate, 2,4-dichloro-6-(o-chloroanilino)-s-triazine, O,O-diethyl phthalimidophosphonothioate, 5-amino-1-[bis(dimethylamino)-phosphinyl]-3-phenyl-1,2,4-triazole, 2,3-dicyano-1,4-dithioanthraquinone, 2-thio-1,3-dithiolo[4,5-b]quinoxaline, methyl 40 1-(butylcarbamoyl)-2-benzimidazolecarbamate, 2-methoxycarbonylaminobenzimidazole, 2-(2-furyl)benzimidazole, 2-(4-thiazolyl)benzimidazole, N-(1,1,2,2-tetrachloroethylthio)tetrahydrophthalimide, N-trichloromethylthiotetrahydrophthalimide, 45 N-trichloromethylthiophthalimide, N-dichlorofluoromethylthio-N',N'-dimethyl-N-phenylsulfamide, 5-ethoxy-3-trichloromethyl-1,2,3-thiadiazole,

00762004 000104
000000 000000

- 2-thiocyanatomethylthiobenzothiazole,
 1,4-dichloro-2,5-dimethoxybenzene,
 4-(2-chlorophenylhydrazono)-3-methyl-5-isoxazolone,
 pyridine-2-thio [sic] 1-oxide, 8-hydroxyquinoline and its copper
 5 salt, 2,3-dihydro-5-carboxanilido-6-methyl-1,4-oxathiine,
 2,3-dihydro-5-carboxanilido-6-methyl-1,4-oxathiine 4,4-dioxide,
 2-methyl-5,6-dihydro-4H-pyran-3-carboxanilide,
 2-methylfuran-3-carboxanilide, 2,5-dimethylfuran-3-carboxanilide,
 2,4,5-trimethylfuran-3-carboxanilide,
 10 N-cyclohexyl-2,5-dimethylfuran-3-carboxamide,
 N-cyclohexyl-N-methoxy-2,5-dimethylfuran-3-carboxamide,
 2-methylbenzanilide, 2-iodobenzanilide, N-formyl-N-morpholine
 2,2,2-trichloroethyl acetal,
 piperazine-1,4-diylbis-1-(2,2,2-trichloroethyl)formamide,
 15 1-(3,4-dichloroanilino)-1-formylamino-2,2,2-trichloroethane,
 2,6-dimethyl-N-tridecylmorpholine and its salts,
 2,6-dimethyl-N-cyclododecylmorpholine and its salts,
 N-[3-(p-tert-butylphenyl)-2-methylpropyl]-cis-2,6-dimethyl-
 morpholine, N-[3-(p-tert-butylphenyl)-2-methylpropyl]piperidine,
 20 1-[2-(2,4-dichlorophenyl)-4-ethyl-1,3-dioxolan-2-ylethyl]-1H-1,2,
 4-triazole,
 1-[2-(2,4-dichlorophenyl)-4-n-propyl-1,3-dioxolan-2-ylethyl]-1H-
 1,2,4-triazole,
 N-(n-propyl)-N-(2,4,6-trichlorophenoxyethyl)-N'-imidazolylurea,
 25 1-(4-chlorophenoxy)-3,3-dimethyl-1-(1H-1,2,4-triazol-1-yl)-2-
 butanone,
 1-(4-chlorophenoxy)-3,3-dimethyl-1-(1H-1,2,4-triazol-1-yl)-2-
 butanol,
 (2RS,3RS)-1-[3-(2-chlorophenyl)-2-(4-fluorophenyl)oxiran-2-yl-
 30 methyl]-1H-1,2,4-triazole,
 a-(2-chlorophenyl)-a-(4-chlorophenyl)-5-pyrimidinemethanol [sic],
 5-butyl-2-dimethylamino-4-hydroxy-6-methylpyrimidine,
 bis(p-chlorophenyl)-3-pyridinemethanol,
 1,2-bis(3-ethoxycarbonyl-2-thioureido)benzene,
 35 1,2-bis(3-methoxycarbonyl-2-thioureido)benzene,

 anilinopyrimidines such as N-(4,6-dimethylpyrimidin-2-yl)aniline,
 N-[4-methyl-6-(1-propynyl)pyrimidin-2-yl]aniline, N-(4-methyl-
 6-cyclopropylpyrimidin-2-yl)aniline,
 40 phenylpyrroles such as
 4-(2,2-difluoro-1,3-benzodioxol-4-yl)pyrrole-3-carbonitrile,

 cinnamamides such as
 45 3-(4-chlorophenyl)-3-(3,4-dimethoxyphenyl)acryloylmorpholine,


10

- and a variety of fungicides, such as dodecylguanidine acetate, 3-[3-(3,5-dimethyl-2-oxycyclohexyl)-2-hydroxyethyl]glutarimide, hexachlorobenzene, methyl N-(2,6-dimethylphenyl)-N-(2-furoyl)-DL-alaninate, DL-N-(2,6-dimethylphenyl)-
- 5 N-(2'-methoxyacetyl)alanine methyl ester, N-(2,6-dimethylphenyl)-N-chloroacetyl-D,L-2-aminobutyrolactone, DL-N-(2,6-dimethylphenyl)-N-(phenylacetyl)alanine methyl ester, 5-methyl-5-vinyl-3-(3,5-dichlorophenyl)-2,4-dioxo-
- 1,3-oxazolidine, 3-[3,5-dichlorophenyl]-
- 10 5-methyl-5-methoxymethyl]-1,3-oxazolidine-2,4-dione [sic], 3-(3,5-dichlorophenyl)-1-isopropylcarbamoylhydantoin, N-(3,5-dichlorophenyl)-1,2-dimethylcyclopropane-
- 1,2-dicarboximide, 2-cyano-[N-(ethylaminocarbonyl)-2-methoximino]acetamide, 1-[2-(2,4-dichlorophenyl)pentyl]-1H-1,2,4-triazole,
- 15 2,4-difluoro-a-(1H-1,2,4-triazolyl-1-methyl)benzhydryl [sic] alcohol, N-(3-chloro-2,6-dinitro-4-trifluoromethylphenyl)-5-trifluoromethyl-3-chloro-2-aminopyridine,
- 1-(bis(4-fluorophenyl)methylsilyl)methyl)-1H-1,2,4-triazole, 2-(4-chlorophenyl)-3-cyclopropyl-1-(1H-1,2,4-triazol-
- 20 1-yl)butan-2-ol, 3-chloro-4-[4-methyl-2-(1H-1,2,4-triazol-1-ylmethyl)-1,3-dioxo- lan-2-yl]phenyl 4-chlorophenyl ether, 1,3-dimethyl-5-chloro-1,3-dimethyl-[2,3-(2,4,4-trimethyltetrahydrofuran)pyrazol-4-carboxanilide], 2',6'-dibromo-2-methyl-
- 4'-trofluoromethoxy-4-trifluoromethylthia-zole-5-carboxanilide
- 25 [sic], [2-(4'-chlorophenyl)-2-chloronicotinilide [sic], N-[(R)-1-(2,4-dichlorophenyl)ethyl]-(S)-2-cyano-
- 3,3-dimethylbutanamide, N-[(R)-1-(4-chlorophenyl)ethyl]- (S)-2,2-cyclopropyl-2',2-dichloro-3'-methylbutanamide, 3-allyloxy-1,2-benzisothiazole 1,1-dioxide,
- 30 2,3-benzisothiadiazole-1-carboxylic acid thiol ester, 1,2,5,6-tetrahydropyrrolo[3,2,1-i,j]quinolin-4-one, 5-methyl-1,2,4-triazolo[3,4-b]benzothiazole, di-idopropyl [sic] 1,3-dithiolan-2-ylidenemalonate,
- 4-(2,2-difluoro-1,3-benzodioxol-4-yl)pyrrole-3-carbonitrile,
- 35 N-(i-propoxycarbonyl)-L-valine-(R)-1-(2-naphthyl)ethylamide, N-(i-propoxycarbonyl)-L-valine-(R,(R,S)-1-(4-methylphenyl)ethyl-
- amide,
- strobilurins such as methyl
- 40 E-methoximino[α-(o-tolyloxy)-o-tolyl]acetate, methyl E-2-[2-[6-(2-cyanophenoxy)pyrimidin-4-yloxy]phenyl]-3-methoxyacrylate, N-methyl E-methoximino[α-(2-phenoxyphenyl)]acetamide, N-methyl E-methoximino[α-(2,5-dimethylphenoxy)-o-tolyl]-acetamide.

11

From amongst the class of the strobilurins, the following fungicidally active compounds of the formula I may preferably be mentioned:

5



10

in which the substituents have the following meanings:

A is NOCH_3 , CHOCH_3 , CHCH_3 ;

15

Y is O, NH;

T is oxygen or oxymethylene;

20

Z is a group X, $\text{N}=\text{C}(\text{R}^1)\text{W}$ or $\text{N}=\text{C}(\text{R}^1)-\text{C}(\text{R}^2)=\text{NOR}^3$;

X is unsubstituted or substituted heterocyclyl, unsubstituted or substituted aryl, unsubstituted or substituted hetaryl;

25

W is unsubstituted or substituted alkyl, unsubstituted or substituted alkenyl, unsubstituted or substituted alkynyl, unsubstituted or substituted cycloalkyl, unsubstituted or substituted cycloalkenyl, unsubstituted or substituted heterocyclyl, unsubstituted or substituted aryl or

30

unsubstituted or substituted hetaryl;

R^1 is hydrogen, cyano, C_1 - C_4 -alkyl, C_1 - C_4 -haloalkyl, C_1 - C_4 -alkoxy, C_1 - C_4 -alkoxy- C_1 - C_4 -alkyl, C_3 - C_6 -cycloalkyl;

35

R^2 is hydrogen, cyano, halogen, $\text{C}(\text{R}^d)=\text{NOR}^3$ or W, OW, SW or NR^cW , where

R^c is hydrogen, alkyl, alkenyl or alkynyl;

40

R^d is hydrogen or alkyl;

R^3 is hydrogen, unsubstituted or substituted alkyl, unsubstituted or substituted alkenyl or unsubstituted or substituted alkynyl

45

where

12

- X is heterocyclyl which may be fully or partially halogenated and/or may carry 1 to 3 of the following radicals:
 cyano, C₁-C₄-alkyl, C₁-C₄-haloalkyl or C₁-C₄-alkoxy;
 aryl, hetaryl, where the cyclic radicals may be partially or
 5 fully halogenated and/or may carry one to three of the following groups:
 cyano, nitro, hydroxyl, mercapto, amino, carboxyl, aminocarbonyl, aminothiocabonyl, C₁-C₆-alkyl, C₁-C₆-haloalkyl, C₁-C₆-alkylcarbonyl, C₁-C₆-alkylsulfonyl,
 10 C₁-C₆-alkylsulfoxyl, C₃-C₆-cycloalkyl, C₁-C₆-alkoxy, C₁-C₆-haloalkoxy, C₁-C₆-alkoxycarbonyl, C₁-C₆-alkylthio, C₁-C₆-alkylamino, di-C₁-C₆-alkylamino, C₁-C₆-alkylaminocarbonyl, di-C₁-C₆-alkylaminocarbonyl, C₁-C₆-alkylaminothiocabonyl, di-C₁-C₆-alkylaminothiocabonyl,
 15 C₂-C₆-alkenyl, C₂-C₆-alkenyloxy, benzyl, benzyloxy, aryl, aryloxy, arylthio, heteroaryl, heteroaryloxy, heteroarylthio, C₃-C₆-alkynyloxy, C₁-C₄-alkylenedioxy, which may be halogenated, or C(=NOR^d)-I₁-R^d where
 R^d is hydrogen or C₁-C₆-alkyl;
 20 I₁ is oxygen, sulfur or NR^d;
 l is 0 or 1 and
 the cyclic groups for their part may be partially or fully halogenated and/or may carry 1 to 3 of the following substituents: cyano, nitro, hydroxyl,
 25 C₁-C₆-alkyl, C₁-C₆-haloalkyl, C₁-C₆-alkylcarbonyl, C₃-C₆-cycloalkyl, C₁-C₆-alkoxy, C₁-C₆-haloalkoxy, C₁-C₆-alkoxycarbonyl, C₁-C₆-alkylthio, C₁-C₆-alkylamino, di-C₁-C₆-alkylamino, C₂-C₆-alkenyl, C₂-C₆-alkenyloxy, C₃-C₆-alkynyloxy and C₁-C₄-alkylenedioxy which may be
 30 halogenated,
 W is C₁-C₆-alkyl, C₂-C₆-alkenyl or C₂-C₆-alkynyl, where these groups may be fully or partially halogenated and/or may carry 1 to 3 of the following radicals:
 35 cyano, C₁-C₆-alkoxy, C₁-C₆-haloalkoxy, C₁-C₆-alkoxycarbonyl, C₃-C₆-cycloalkyl, heterocyclyl, aryl or hetaryl, where
 the cyclic groups for their part may be partially or fully halogenated and/or may carry 1 to 3 of the following radicals:
 40 cyano, nitro, C₁-C₄-alkyl, C₁-C₄-haloalkyl, C₁-C₄-alkoxy, C₁-C₄-haloalkoxy; or
 is C₃-C₆-cycloalkyl, C₃-C₆-cycloalkenyl or heterocyclyl, where these groups may be fully or partially halogenated and/or may carry 1 to 3 of the following radicals:
 45 cyano, C₁-C₄-alkyl, C₁-C₄-haloalkyl or C₁-C₄-alkoxy;
 or
 is aryl or heteroaryl,

where these radicals may be partially or fully halogenated and/or may carry one to three of the following groups:

- cyano, nitro, hydroxyl, mercapto, amino, carboxyl, aminocarbonyl, aminothiocabonyl, C₁-C₆-alkyl,
- 5 C₁-C₆-haloalkyl, C₁-C₆-alkylcarbonyl, C₁-C₆-alkylsulfonyl, C₁-C₆-alkylsulfoxyl, C₃-C₆-cycloalkyl, C₁-C₆-alkoxy, C₁-C₆-haloalkoxy, C₁-C₆-alkoxycarbonyl, C₁-C₆-alkylthio, C₁-C₆-alkylamino, di-C₁-C₆-alkylamino, C₁-C₆-alkylaminocarbonyl, di-C₁-C₆-alkylaminocarbonyl, C₁-C₆-alkylaminothiocabonyl, di-C₁-C₆-alkylaminothiocabonyl,
- 10 C₂-C₆-alkenyl, C₂-C₆-alkenyloxy, benzyl, benzyloxy, aryl, aryloxy, arylthio, heteroaryl, heteroaryloxy, heteroarylthio, C₃-C₆-alkynyloxy, C₁-C₄-alkylenedioxy, which may be halogenated, or C(=NOR^d)-I₁-R^d where
- 15 R^d is hydrogen or C₁-C₆-alkyl;
I is oxygen, sulfur or NR^d;
1 is 0 or 1 and
- the cyclic groups for their part may be partially or fully halogenated and/or may carry 1 to 3 of the
- 20 following substituents:
cyano, nitro, hydroxyl, C₁-C₆-alkyl, C₁-C₆-haloalkyl, C₁-C₆-alkylcarbonyl, C₃-C₆-cycloalkyl, C₁-C₆-alkoxy, C₁-C₆-haloalkoxy, C₁-C₆-alkoxycarbonyl, C₁-C₆-alkylthio, C₁-C₆-alkylamino, di-C₁-C₆-alkylamino, C₂-C₆-alkenyl,
- 25 C₂-C₆-alkenyloxy, C₃-C₆-alkynyloxy and C₁-C₄-alkylenedioxy which may be halogenated,
- R² is hydrogen, cyano, halogen, C(R^d)=NOR³ or W, OW, SW or NR^cW, where
- 30 R^c is hydrogen, C₁-C₆-alkyl, C₂-C₆-alkenyl or C₂-C₆-alkynyl;
R^d is hydrogen or C₁-C₄-alkyl; and
- R³ is hydrogen, C₁-C₆-alkyl, C₁-C₆-cyanoalkyl, C₂-C₆-alkenyl, C₂-C₆-alkynyl, C₁-C₄-alkoxy-C₁-C₆-alkyl or C₃-C₆-cycloalkyl-C₁-C₄-alkyl, where
- 35 these groups may be partially or fully halogenated and the cycloalkyl groups may additionally carry 1 to 3 C₁-C₄-alkyl radicals;

and their salts.

40 Collective terms represent the following substituents:

Halogen: fluorine, chlorine, bromine and iodine;

Alkyl: saturated, straight-chain or branched hydrocarbon radicals

45 having 1 to 4, 6 or 10 carbon atoms, for example C₁-C₆-alkyl such as methyl, ethyl, propyl, 1-methylethyl, butyl, 1-methylpropyl, 2-methylpropyl, 1,1-dimethylethyl, pentyl, 1-methylbutyl,

00762044-000101

2-methylbutyl, 3-methylbutyl, 2,2-dimethylpropyl, 1-ethylpropyl, hexyl, 1,1-dimethylpropyl, 1,2-dimethylpropyl, 1-methylpentyl, 2-methylpentyl, 3-methylpentyl, 4-methylpentyl, 1,1-dimethylbutyl, 1,2-dimethylbutyl, 1,3-dimethylbutyl, 2,2-dimethylbutyl, 2,3-dimethylbutyl, 3,3-dimethylbutyl, 1-ethylbutyl, 2-ethylbutyl, 1,1,2-trimethylpropyl, 1,2,2-trimethylpropyl, 1-ethyl-1-methylpropyl and 1-ethyl-2-methylpropyl;

Haloalkyl: straight-chain or branched alkyl groups having 1 to 10 carbon atoms (as mentioned above), where the hydrogen atoms in these groups may be partially or fully replaced by halogen atoms as mentioned above, for example C₁-C₂-haloalkyl such as chloromethyl, bromomethyl, dichloromethyl, trichloromethyl, fluoromethyl, difluoromethyl, trifluoromethyl, chlorofluoromethyl, 1,2-dichlorofluoromethyl, chlorodifluoromethyl, 1-chloroethyl, 1-bromoethyl, 1-fluoroethyl, 2-fluoroethyl, 2,2-difluoroethyl, 2,2,2-trifluoroethyl, 2-chloro-2-fluoroethyl, 2-chloro-2,2-difluoroethyl, 2,2-dichloro-2-fluoroethyl, 2,2,2-trichloroethyl and pentafluoroethyl;

20

Alkoxy: straight-chain or branched alkyl groups having 1 to 10 carbon atoms (as mentioned above) which are attached to the skeleton via an oxygen atom (-O-);

25 **Haloalkoxy:** straight-chain or branched haloalkyl groups having 1 to 10 carbon atoms (as mentioned above) which are attached to the skeleton via an oxygen atom (-O-);

Alkylthio: straight-chain or branched alkyl groups having 1 to 10 or 1 to 4 carbon atoms (as mentioned above) which are attached to the skeleton via a sulfur atom (-S-);

Alkylamino: a straight-chain or branched alkyl group having 1 to 10 carbon atoms (as mentioned above) which is attached to the skeleton via an amino group (-NH-);

Dialkylamino: two independent straight-chain or branched alkyl groups having in each case 1 to 10 carbon atoms (as mentioned above) which are attached to the skeleton via a nitrogen atom;

40

Alkylcarbonyl: a straight-chain or branched alkyl group having 1 to 10 carbon atoms (as mentioned above) which is attached to the skeleton via a carbonyl group (-CO-);

45

Alkoxy carbonyl: an alkoxy group having 1 to 10 carbon atoms (as mentioned above) which is attached to the skeleton via a carbonyl group (-CO-);

- 5 **Alkylthio carbonyl:** an alkylthio group having 1 to 10 carbon atoms (as mentioned above) which is attached to the skeleton via a carbonyl group (-CO-);

- Alkylaminocarbonyl:** an alkylamino group having 1 to 10 carbon atoms (as mentioned above) which is attached to the skeleton via a carbonyl group (-CO-);

Dialkylaminocarbonyl: a dialkylamino group (as mentioned above) which is attached to the skeleton via a carbonyl group (-CO-);

15

Alkyl carbonyloxy: a straight-chain or branched alkyl group having 1 to 10 carbon atoms (as mentioned above) which is attached to the skeleton via a carbonyloxy group (-CO₂-);

- 20 **Alkyl sulfonyl:** a straight-chain or branched alkyl group having 1 to 10 carbon atoms (as mentioned above) which is attached to the skeleton via a sulfonyl group (-SO₂-);

- Alkoxy sulfonyl:** an alkoxy group having 1 to 10 carbon atoms (as mentioned above) which is attached to the skeleton via a sulfonyl group (-SO₂-);

- Alkenyl:** unsaturated, straight-chain or branched hydrocarbon radicals having 2 to 4, 6, 8 or 10 carbon atoms and a double bond in any position, for example C₂-C₆-alkenyl such as ethenyl, 1-propenyl, 2-propenyl, 1-methylethenyl, 1-butenyl, 2-butenyl, 3-butenyl, 1-methyl-1-propenyl, 2-methyl-1-propenyl, 1-methyl-2-propenyl, 2-methyl-2-propenyl, 1-pentenyl, 2-pentenyl, 3-pentenyl, 4-pentenyl, 1-methyl-1-butenyl, 2-methyl-1-butenyl, 3-methyl-1-butenyl, 1-methyl-2-butenyl, 2-methyl-2-butenyl, 3-methyl-2-butenyl, 1-methyl-3-butenyl, 2-methyl-3-butenyl, 3-methyl-3-butenyl, 1,1-dimethyl-2-propenyl, 1,2-dimethyl-1-propenyl, 1,2-dimethyl-2-propenyl, 1-ethyl-1-propenyl, 1-ethyl-2-propenyl, 1-hexenyl, 2-hexenyl, 3-hexenyl, 4-hexenyl, 5-hexenyl, 1-methyl-1-pentenyl, 2-methyl-1-pentenyl, 3-methyl-1-pentenyl, 4-methyl-1-pentenyl, 1-methyl-2-pentenyl, 2-methyl-2-pentenyl, 3-methyl-2-pentenyl, 4-methyl-2-pentenyl, 1-methyl-3-pentenyl, 2-methyl-3-pentenyl, 3-methyl-3-pentenyl, 4-methyl-3-pentenyl, 1-methyl-4-pentenyl, 2-methyl-4-pentenyl, 3-methyl-4-pentenyl, 4-methyl-4-pentenyl, 1,1-dimethyl-2-butenyl, 1,1-dimethyl-3-butenyl, 1,2-dimethyl-1-butenyl, 1,2-dimethyl-2-butenyl, 1,2-dimethyl-3-butenyl, 1,3-dimethyl-1-butenyl,

16

1,3-dimethyl-2-butenyl, 1,3-dimethyl-3-butenyl, 2,2-dimethyl-3-butenyl, 2,3-dimethyl-1-butenyl, 2,3-dimethyl-2-butenyl, 2,3-dimethyl-3-butenyl, 3,3-dimethyl-1-butenyl, 3,3-dimethyl-2-butenyl, 1-ethyl-1-butenyl, 1-ethyl-2-butenyl, 1-ethyl-3-butenyl, 2-ethyl-1-butenyl, 2-ethyl-2-butenyl, 2-ethyl-3-butenyl, 1,1,2-trimethyl-2-propenyl, 1-ethyl-1-methyl-2-propenyl, 1-ethyl-2-methyl-1-propenyl and 1-ethyl-2-methyl-2-propenyl;

10 **Haloalkenyl:** unsaturated, straight-chain or branched hydrocarbon radicals having 2 to 10 carbon atoms and a double bond in any position (as mentioned above), where the hydrogen atoms in these groups may be partly or fully replaced by halogen atoms as mentioned above, in particular by fluorine, chlorine and bromine;

15 **Alkenyloxy:** unsaturated, straight-chain or branched hydrocarbon
radicals having 3 to 10 carbon atoms and a double bond in any
position which is not adjacent to the hetero atom (as mentioned
above), which are attached to the skeleton via an oxygen atom
20 (-O-);

Haloalkenyloxy: unsaturated, straight-chain or branched alkenyloxy groups having 3 to 10 carbon atoms (as mentioned above), where the hydrogen atoms in these groups may be partly or 25 fully replaced by halogen atoms, in particular by fluorine, chlorine and bromine;

Alkenylthio: unsaturated, straight-chain or branched hydrocarbon radicals having 3 to 10 carbon atoms and a double bond in any position which is not adjacent to the hetero atom (as mentioned above), which are attached to the skeleton via a sulfur atom (-S-);

Alkenylamino: unsaturated, straight-chain or branched hydrocarbon radicals having 3 to 10 carbon atoms and a double bond in any position which is not adjacent to the hetero atom (as mentioned above), which are attached to the skeleton via an amino group (-NH-);

40 **Alkenylcarbonyl:** unsaturated, straight-chain or branched hydrocarbon radicals having 2 to 10 carbon atoms and a double bond in any position (as mentioned above), which are attached to the skeleton via a carbonyl group (-CO-);

Alkenyloxy carbonyl: straight-chain or branched alkenyloxy groups having 3 to 10 carbon atoms (as mentioned above) which are attached to the skeleton via a carbonyl group (-CO-);

- 5 **Alkenylthiocarbonyl:** straight-chain or branched alkenylthio groups having 3 to 10 carbon atoms (as mentioned above) which are attached to the skeleton via a carbonyl group (-CO-);

- Alkenylaminocarbonyl:** straight-chain or branched alkenylamino groups having 3 to 10 carbon atoms (as mentioned above) which are attached to the skeleton via a carbonyl group (-CO-);

- Alkenylcarbonyloxy:** unsaturated, straight-chain or branched hydrocarbon radicals having 2 to 10 carbon atoms and a double bond in any position (as mentioned above), which is [sic] attached to the skeleton via a carbonyloxy group (-CO₂-);

- Alkynyl:** straight-chain or branched hydrocarbon groups having 2 to 4, 6, 8 or 10 carbon atoms and a triple bond in any position, 20 for example C₂-C₆-alkynyl such as ethynyl, 1-propynyl, 2-propynyl, 1-butynyl, 2-butynyl, 3-butynyl, 1-methyl-2-propynyl, 1-pentynyl, 2-pentynyl, 3-pentynyl, 4-pentynyl, 1-methyl-2-butynyl, 1-methyl-3-butynyl, 2-methyl-3-butynyl, 3-methyl-1-butynyl, 1,1-dimethyl-2-propynyl, 1-ethyl-2-propynyl, 1-hexynyl, 2-hexynyl, 3-hexynyl, 25 4-hexynyl, 5-hexynyl, 1-methyl-2-pentynyl, 1-methyl-3-pentynyl, 1-methyl-4-pentynyl, 2-methyl-3-pentynyl, 2-methyl-4-pentynyl, 3-methyl-1-pentynyl, 3-methyl-4-pentynyl, 4-methyl-1-pentynyl, 4-methyl-2-pentynyl, 1,1-dimethyl-2-butynyl, 1,1-dimethyl-3-butynyl, 1,2-dimethyl-3-butynyl, 2,2-dimethyl-3-butynyl, 30 3,3-dimethyl-1-butynyl, 1-ethyl-2-butynyl, 1-ethyl-3-butynyl, 2-ethyl-3-butynyl and 1-ethyl-1-methyl-2-propynyl;

- Haloalkynyl:** unsaturated, straight-chain or branched hydrocarbon radicals having 2 to 10 carbon atoms and a triple bond in any 35 position (as mentioned above), where the hydrogen atoms in these groups may be partly or fully replaced by halogen atoms, in particular by fluorine, chlorine and bromine;

- Alkynyloxy:** unsaturated, straight-chain or branched hydrocarbon 40 radicals having 3 to 10 carbon atoms and a triple bond in any position which is not adjacent to the hetero atom (as mentioned above), which are attached to the skeleton via an oxygen atom (-O-);

- 45 **Haloalkynyloxy:** unsaturated, straight-chain or branched alkynyloxy groups having 3 to 10 carbon atoms (as mentioned above), where the hydrogen atoms in these groups may be partly or

fully replaced by halogen atoms as mentioned above, in particular by fluorine, chlorine and bromine;

Cycloalkyl: monocyclic, saturated hydrocarbon groups having 3 to 6, 8, 10 or 12 carbon ring members, for example C₃-C₈-cycloalkyl such as cyclopropyl, cyclobutyl, cyclopentyl, cyclohexyl, cycloheptyl and cyclooctyl;

Cycloalkoxy: monocyclic, saturated hydrocarbon groups having 3 to 12 carbon ring members (as mentioned above) which are attached to the skeleton via an oxygen atom (-O-);

Cycloalkylthio: monocyclic, saturated hydrocarbon groups having 3 to 12 carbon ring members (as mentioned above) which are attached to the skeleton via a sulfur atom (-S-);

Cycloalkylamino: monocyclic, saturated hydrocarbon groups having 3 to 12 carbon ring members (as mentioned above) which are attached to the skeleton via an amino group (-NH-);

Cycloalkylcarbonyl: monocyclic, saturated hydrocarbon groups having 3 to 12 carbon ring members (as mentioned above) which are attached to the skeleton via a carbonyl group (-CO-);

Cycloalkoxycarbonyl: a monocyclic cycloalkoxy group having 3 to 12 carbon ring members (as mentioned above) which is attached to the skeleton via a carbonyl group (-CO-);

Cycloalkylthiocarbonyl: a monocyclic cycloalkylthio group having 3 to 12 carbon ring members (as mentioned above) which is attached to the skeleton via a carbonyl group (-CO-);

saturated or partially unsaturated cyclic radical which, in addition to carbon atoms, may contain hetero atoms from the group consisting of oxygen, sulfur or nitrogen as ring members: cycloalkyl having 3 to 12 carbon ring members as mentioned above or 5- or 6-membered heterocycles (heterocyclyl) containing, in addition to carbon ring members, one to three nitrogen atoms and/or one oxygen or sulfur atom or one or two oxygen and/or sulfur atoms, for example 2-tetrahydrofuranyl, 3-tetrahydrofuranyl, 2-tetrahydrothienyl, 3-tetrahydrothienyl, 2-pyrrolidinyl, 3-pyrrolidinyl, 3-isoxazolidinyl, 4-isoxazolidinyl, 5-isoxazolidinyl, 3-isothiazolidinyl, 4-isothiazolidinyl, 5-isothiazolidinyl, 3-pyrazolidinyl, 4-pyrazolidinyl, 5-pyrazolidinyl, 2-oxazolidinyl, 4-oxazolidinyl, 5-oxazolidinyl, 2-thiazolidinyl, 4-thiazolidinyl, 5-thiazolidinyl, 2-imidazolidinyl, 4-imidazolidinyl,

- 1,2,4-oxadiazolidin-3-yl, 1,2,4-oxadiazolidin-5-yl,
 1,2,4-thiadiazolidin-3-yl, 1,2,4-thiadiazolidin-5-yl,
 1,2,4-triazolidin-3-yl, 1,3,4-oxadiazolidin-2-yl,
 1,3,4-thiadiazolidin-2-yl, 1,3,4-triazolidin-2-yl,
 5 2,3-dihydrofurfur-2-yl, 2,3-dihydrofurfur-3-yl, 2,4-dihydrofurfur-2-yl,
 2,4-dihydrofurfur-3-yl, 2,3-dihydrothien-2-yl, 2,3-dihydro-
 thien-3-yl, 2,4-dihydrothien-2-yl, 2,4-dihydrothien-3-yl,
 2,3-pyrrolin-2-yl, 2,3-pyrrolin-3-yl, 2,4-pyrrolin-2-yl,
 2,4-pyrrolin-3-yl, 2,3-isoxazolin-3-yl, 3,4-isoxazolin-3-yl,
 10 4,5-isoxazolin-3-yl, 2,3-isoxazolin-4-yl, 3,4-isoxazolin-4-yl,
 4,5-isoxazolin-4-yl, 2,3-isoxazolin-5-yl, 3,4-isoxazolin-5-yl,
 4,5-isoxazolin-5-yl, 2,3-isothiazolin-3-yl, 3,4-iso-
 thiazolin-3-yl, 4,5-isothiazolin-3-yl, 2,3-isothiazolin-4-yl,
 3,4-isothiazolin-4-yl, 4,5-isothiazolin-4-yl, 2,3-iso-
 15 thiazolin-5-yl, 3,4-isothiazolin-5-yl, 4,5-isothiazolin-5-yl,
 2,3-dihydropyrazol-1-yl, 2,3-dihydropyrazol-2-yl, 2,3-dihydro-
 pyrazol-3-yl, 2,3-dihydropyrazol-4-yl, 2,3-dihydropyrazol-5-yl,
 3,4-dihydropyrazol-1-yl, 3,4-dihydropyrazol-3-yl, 3,4-dihydro-
 pyrazol-4-yl, 3,4-dihydropyrazol-5-yl, 4,5-dihydropyrazol-1-yl,
 20 4,5-dihydropyrazol-3-yl, 4,5-dihydropyrazol-4-yl, 4,5-dihydro-
 pyrazol-5-yl, 2,3-dihydrooxazol-2-yl, 2,3-dihydrooxazol-3-yl,
 2,3-dihydrooxazol-4-yl, 2,3-dihydrooxazol-5-yl, 3,4-dihydro-
 oxazol-2-yl, 3,4-dihydrooxazol-3-yl, 3,4-dihydrooxazol-4-yl,
 3,4-dihydrooxazol-5-yl, 3,4-dihydrooxazol-2-yl, 3,4-dihydro-
 25 oxazol-3-yl, 3,4-dihydrooxazol-4-yl, 2-piperidinyl,
 3-piperidinyl, 4-piperidinyl, 1,3-dioxan-5-yl, 2-tetrahydro-
 pyranyl, 4-tetrahydropyranyl, 2-tetrahydrothienyl, 3-tetrahydro-
 pyridazinyl, 4-tetrahydropyridazinyl, 2-tetrahydropyrimidinyl,
 4-tetrahydropyrimidinyl, 5-tetrahydropyrimidinyl, 2-tetrahydro-
 30 pyrazinyl, 1,3,5-tetrahydrotriazin-2-yl and 1,2,4-tetrahydro-
 triazin-3-yl;

Aryl: a mono- to tricyclic aromatic ring system containing 6 to 14 carbon ring members, for example phenyl, naphthyl and

35 anthracenyl;

Aryloxy: a mono- to tricyclic aromatic ring system (as mentioned above) which is attached to the skeleton via an oxygen atom (-O-);

40

Arylthio: a mono- to tricyclic aromatic ring system (as mentioned above) which is attached to the skeleton via a sulfur atom (-S-);

Arylamino: a mono- to tricyclic aromatic ring system (as

45 mentioned above) which is attached to the skeleton via an amino group (-NH-);

20

Arylcarbonyl: a mono- to tricyclic aromatic ring system (as mentioned above) which is attached to the skeleton via a carbonyl group (-CO-);

- 5 **Aryloxycarbonyl:** a mono- to tricyclic aryloxy group (as mentioned above) which is attached to the skeleton via a carbonyl group (-CO-);

- Arylthiocarbonyl:** a mono- to tricyclic arylthio group (as mentioned above) which is attached to the skeleton via a carbonyl group (-CO-);

- Arylamino carbonyl:** a mono- to tricyclic arylamino group (as mentioned above) which is attached to the skeleton via a carbonyl group (-CO-);

- Arylcarbonyloxy:** a mono- to tricyclic aromatic ring system (as mentioned above) which is attached to the skeleton via a carbonyloxy group (-CO₂-);

20

Arylcarbonylthio: a mono- to tricyclic aromatic ring system (as mentioned above) which is attached to the skeleton via a carbonylthio group (-COS-);

- 25 **Arylcarbonylamino:** a mono- to tricyclic aromatic ring system (as mentioned above) which is attached to the skeleton via a carbonylamino group (-CONH-);

- Arylsulfonyl:** a mono- to tricyclic aromatic ring system (as mentioned above) which is attached to the skeleton via a sulfonyl group (-SO₂-);

- Aryloxysulfonyl:** a mono- to tricyclic aryloxy group (as mentioned above) which is attached to the skeleton via a sulfonyl group (-SO₂-);

aromatic ring system which, in addition to carbon ring members, may contain hetero atoms from the group consisting of oxygen, sulfur and nitrogen: aryl as mentioned above or mono- or bicyclic heteroaryl, for example

- 5-membered hetaryl containing one to four nitrogen atoms or one to three nitrogen atoms and one sulfur or oxygen atom:
5-membered hetaryl ring groups which, besides carbon atoms, can contain one to four nitrogen atoms or one to three nitrogen atoms and one sulfur or oxygen atom as ring members,
45 for example, 2-furyl, 3-furyl, 2-thienyl, 3-thienyl, 2-pyrrolyl, 3-pyrrolyl, 3-isoxazolyl, 4-isoxazolyl,

- 5-isoxazolyl, 3-isothiazolyl, 4-isothiazolyl, 5-isothiazolyl, 3-pyrazolyl, 4-pyrazolyl, 5-pyrazolyl, 2-oxazolyl, 4-oxazolyl, 5-oxazolyl, 2-thiazolyl, 4-thiazolyl, 5-thiazolyl, 2-imidazolyl, 4-imidazolyl,
- 1,2,4-oxadiazol-3-yl, 1,2,4-oxadiazol-5-yl, 1,2,4-thiadiazol-3-yl, 1,2,4-thiadiazol-5-yl, 1,2,4-triazol-3-yl, 1,3,4-oxadiazol-2-yl, 1,3,4-thiadiazol-2-yl, 1,3,4-triazol-2-yl;
- benzo-fuzed 5-membered hetaryl containing one to three
- 10 nitrogen atoms or one nitrogen atom and one oxygen or sulfur
atom: 5-membered hetaryl groups which, besides carbon atoms, can also contain one to four nitrogen atoms or one to three nitrogen atoms and one sulfur or oxygen atom as ring members and in which two adjacent carbon ring members or one nitrogen and an adjacent carbon ring member can be bridged by a
- 15 buta-1,3-diene-1,4-diyl group;
- 5-membered hetaryl, bonded via nitrogen and containing one to four nitrogen atoms, or benzo-fuzed 5-membered hetaryl, bonded via nitrogen and containing one to three nitrogen
- 20 atoms: 5-membered hetaryl groups which, besides carbon atoms, can contain one to four nitrogen atoms, or one to three nitrogen atoms, respectively, as ring members and in which two adjacent carbon ring members or one nitrogen and an adjacent carbon ring member can be bridged by a
- 25 buta-1,3-diene-1,4-diyl group, these rings being bonded to the skeleton via one of the nitrogen ring members;
- 6-membered hetaryl containing one to three, or one to four, nitrogen atoms: 6-membered hetaryl ring groups which, besides carbon atoms, can contain one to three, or one to four,
- 30 nitrogen atoms as ring members, for example 2-pyridinyl, 3-pyridinyl, 4-pyridinyl, 3-pyridazinyl, 4-pyridazinyl, 2-pyrimidinyl, 4-pyrimidinyl, 5-pyrimidinyl, 2-pyrazinyl, 1,3,5-triazin-2-yl and 1,2,4-triazin-3-yl.
- 35 As for the remaining substituents, these correspond to the substituents described in WO/15552.

Other suitable fungicidal crop protection active ingredients are:

- 40 (+)-cis-1-(4-chlorophenyl)-2-(1H-1,2,4-triazol-1-yl)cycloheptanol, metsulfonax, cyprodinil, methyl
- (E)-2-{2-[6-(2-cyanophenoxy)pyrimidin-4-yloxy]phenyl}-3-methoxyacrylate and the azole active ingredients
- N-propyl-N-[2,4,6-trichlorophenoxy]ethyl]imidazole-1-carboxamide
- 45 (prochloraz),
- (Z)-2-(1,2,4-triazol-1-ylmethyl)-2-(4-fluorophenyl)-3-(2-chlorophenyl)oxirane (epoxiconazole),

- 1-butyl-1-(2,4-dichlorophenyl)-2-(1,2,4-triazol-1-yl)ethanol
(hexaconazole), 1-[(2-chlorophenyl)methyl]-1-(1,1-dimethyl)-2-(
1,2,4-triazol-1-yl)ethanol),
1-(4-fluorophenyl)-1-(2-fluorophenyl)-2-(1,2,4-triazol-1-yl)-
5 ethanol (flutriafol),
(RS)-4-(4-chlorophenyl)-2-phenyl-2-(1H-1,2,4-triazol-1-ylmethyl)-
butyronitrile, 1-[(2 RS, 4 RS; 2 RS, 4 SR)-4-bromo-2-(2,4-
dichlorophenyl)tetrahydrofurfuryl]-1H-1,2,4-triazole [sic],
3-(2,4-dichlorophenyl)-2-(1H-1,2,4-triazol-1-yl)quinazolin-4-
10 (3H)-one,
(RS)-2,2-dimethyl-3-(2-chlorobenzyl)-4-(1H-1,2,4-triazol-1-yl)-
butan-3-ol, bitertanol, triadimefon, triadimenol, bromuconazole,
cyproconazole, dichlobutrazole, difenoconazole, diniconazole,
etaconazole, fluquinconazole, imibenconazole, propiconazole,
15 flusilazole, tebuconazole, imazalil, penconazole, tetraconazole,
triflumizol, metconazole, fluquinconazole, fenbuconazole,
triticonazole.

- The fungicidal crop protection active ingredients are preferably
20 from the group consisting of: tridemorph, fenpropimorph,
fenpropidine and the azole active ingredients, it being possible
for one or more active ingredients amongst the group consisting
of tridemorph, fenpropimorph and fenpropidine to be present in
the soil-applied CR granules according to the invention.


- 25 The following are preferred amongst the azole active ingredients:
prochloraz, epoxiconazole, hexaconazole, cyproconazole,
difenoconazole, propiconazole, flusilazole, diniconazole,
triticonazole and tebuconazole, the use of epoxiconazole being
30 especially advantageous.

- Also suitable are valinamide active ingredients, preferably:
N¹-[1-(4-chlorophenyl)-1-ethyl]-N²-isopropoxycarbonyl-L-valinamide,
N¹-[1-(4-methylphenyl)-1-ethyl]-N²-isopropoxycarbonyl-L-valinamide,
35 N¹-[1-(4-methoxyphenyl)-1-ethyl]-N²-isopropoxycarbonyl-L-
valinamide,
N¹-[1-R-(2-naphthyl)-1-ethyl]-N²-isopropoxycarbonyl-L-valinamide.

- Preferred amongst the group of the resistance activators is Bion®
40 (5-methyl [sic] benzo[1,2,3]thiadiazole-7-carbothioate).

The following compounds of formula III are preferably employed
from amongst the group of the salicylates:

23



(III)

5


10 in which R^9 is:

- n-, i- or tert- C_1-C_8 -alkyl, C_1-C_8 -alkoxyalkyl or C_1-C_8 -haloalkyl,
 n- or i- C_1-C_8 -alkylcarbonyl, preferably acetyl, propionyl,
 benzoyl, C_1-C_8 -alkylbenzoyl, C_1-C_8 -haloalkylbenzoyl,
 15 C_1-C_8 -alkoxybenzoyl or hydrogen, hydroxycarbonyl- C_1-C_4 -alkyl,
 C_1-C_4 -alkoxycarbonyl- C_1-C_4 -alkyl,

- R^{10} can be hydroxyl, n- or i- or tert- C_1-C_8 -alkyloxy,
 C_1-C_8 -haloalkyloxy, C_1-C_4 -alkoxy- C_1-C_4 -alkoxy, furthermore amino,
 20 C_1-C_8 -alkylcarbonylamino or substituted or unsubstituted
 arylcarbonylamino or, preferably, benzoylamino, C_1-C_6 -alkylamino,
 di- C_1-C_6 -alkylamino, substituted (1-3 substituents selected from
 the group consisting of halogen, CN, NO_2 , OH, NH_2 , CO_2H , $CONH_2$,
 C_1-C_4 -alkyl, C_1-C_4 -haloalkyl, C_1-C_4 -alkoxy, C_1-C_4 -haloalkoxy,
 25 C_1-C_4 -alkoxycarbonyl, C_1-C_4 -alkylamino, di- C_1-C_4 -alkylamino) or
 unsubstituted arylamino (in particular phenylamino).

R^{11} independently of one another can be:

- hydrogen, fluorine, chlorine or iodine, n- or i- or tert-
 30 C_1-C_8 -alkyl, C_1-C_8 -alkoxyalkyl or C_1-C_8 -haloalkyl, furthermore an
 aryl radical of formula IV,



(IV)

35

40

which is unsubstituted or mono- or up to trisubstituted and in
 which the index m or n can be 0-3 and the radical R^{12} has the
 meaning given for R^{11} .

45 Especially preferred are the compounds:

acetylsalicylic acid, salacetamide, salicylamide, ethenzamide
diflunisal, salicylanilide and (2-carbamoylphenoxy)acetic acid.

- The crop protection active ingredients may also be in the form of
5 their salts or metal complexes. The invention also extends to the
compositions obtained in this manner.

- The salts are prepared by reaction with acids, for example
hydrohalic acids such as hydrofluoric acid, hydrochloric acid,
10 hydrobromic acid or hydroiodic acid, or sulfuric acid, phosphoric
acid, nitric acid or organic acids such as acetic acid,
trifluoroacetic acid, trichloroacetic acid, propionic acid,
glycolic acid, lactic acid, succinic acid, citric acid, benzoic
acid, cinnamic acid, oxalic acid, formic acid, benzenesulfonic
15 acid, p-toluenesulfonic acid, methanesulfonic acid, salicylic
acid, p-aminosalicylic acid or 1,2-naphthalenedisulfonic acid.

- Metal complexes can optionally contain just one or else more than
one crop protection active ingredient. It is also possible to
20 prepare metal complexes which contain these active ingredients
together in the form of a mixed complex.

- Metal complexes are prepared from the organic molecule on which
they are based and an inorganic or organic metal salt, for
25 example the halides, nitrates, sulfates, phosphates, acetates,
trifluoroacetates, trichloroacetates, propionates, tartrates,
sulfonates, salicylates or benzoates of the metals of the second
Main Group such as calcium and magnesium and the third and fourth
Main Group such as aluminum, tin or lead, and the first to eighth
30 B group such as chromium, manganese, iron, cobalt, nickel, copper
and zinc. Preferred are the B group elements of the 4th period,
in particular copper. The metals can exist in the various
valences which they can assume. The metal complexes can contain
one or more organic moieties as ligand.

- 35 Control of harmful fungi with the soil-applied CR granules
according to the invention is expediently carried out in such a
manner that a fungicidally active amount of the soil-applied CR
granules is allowed to act in or on the soil, on the seed applied
40 to the soil, or on the plants developing therefrom, or on
seedlings.

- In the case of annual plants, the soil-applied CR granules
according to the invention are preferably applied concomitantly
45 with sowing. Modification of the commercially available seed
drills allows the granules to be applied in the same drill
coulters together with the seed. Thus, the soil-applied CR

granules according to the invention are deposited at the same or different depth as the seed. The number of active-ingredient-comprising granules per seed kernel may vary. The seed drills are equipped with a separate tank for the soil-applied CR granules according to the invention. The bulk of the soil-applied CR granules according to the invention is separated into individual granules via a metering device which is similar to the seed metering device and fed to the common drill coulter via a separate tube. Commercially available drilling systems for seed and granules which have been developed for the concomitant application of fertilizers and seeds may be employed as the seed drills.

The controlled release of the active ingredients allows the release rate of the active ingredients in the soil to be controlled in such a way that, for example in the case of the fungicidal crop protection active ingredients, effective protection against fungal diseases can be maintained over the entire vegetation period. Active ingredient is taken up continuously via the roots to the same extent as the active ingredients are released, from the active ingredients formulated according to the invention, in a controlled fashion, and, via the roots, the active ingredients are then distributed systemically within the plant.

The process according to the invention has the following advantages over spray application of the crop protection active ingredients, which is widely used for controlling fungi:

- 30 - A single application into the soil, of the active ingredients formulated according to the invention, which preferably takes place concomitantly with the seed or with the planting of seedlings, allows an effective protection of the plant over the entire vegetation period to be achieved, for example against fungal diseases.
- 35 - This dispenses with the hitherto customary application of several spray applications to the growing crop, thus allowing a considerable saving of labor.
- 40 - Application of the crop protection active ingredients in the form of the formulation according to the invention may result in smaller amounts of active ingredients to be applied.

45

00762044-000104

- A drift of the crop protection active ingredients - as is encountered during spray application - is excluded by this application.
- 5 - The use of the process according to the invention may dispense with seed dressing.

- The soil-applied CR granules according to the invention are preferably produced as coated granules by first applying the
- 10 active ingredients to solid, granular carriers. The resulting active-ingredient-comprising granules are subsequently coated with suitable coating substances which cause a delayed, controlled release of active ingredient.
 - 15 Examples of suitable solid carriers for the soil-applied CR granules according to the invention are mineral earths such as silica gel, silicas, silica gels [sic], silicates, talc, kaolin, limestone, lime, chalk, bole, sand, loess, clay, dolomite, diatomaceous earth, calcium sulfate, magnesium sulfate, magnesium
 - 20 oxide, ground synthetic substances, fertilizers such as ammonium sulfate, ammonium phosphate, ammonium nitrate, ureas, for example crotonylidenediurea, isobutylidenediurea, and plant products such as cereal meal, corn meal, tree bark meal, wood meal and nutshell meal, corn grits, cellulose powder, fertilizers. Preferred as
 - 25 carriers are fertilizer granules or fertilizer pellets, in particular those which contain phosphate. Sand is very especially preferred.

- In general, the granules have a particle diameter of 0.1 to
- 30 10 mm, preferably 0.5 to 8 mm, in particular 0.5 to 3 mm.

- As a rule, the active ingredients are applied to the carriers in such a manner that they are sprayed on in the form of
- oil-in-water emulsions, emulsion concentrates, suspensions,
 - 35 suspension concentrates or as a solution in organic solvents or, preferably, in water.

- Spraying takes place, for example, in fluidized-bed coaters or in drums or rotating disks in which the carrier granules are rolled,
- 40 in perforated vats with controlled drying medium supply, expediently air, or nitrogen. In general, temperatures between 30°C and 180°C, preferably 35°C to 90°C, are used for spraying-on and for drying.
 - 45 The active-ingredient-comprising granules can be manufactured as carrier granules.

- In principle, carrier granules are composed of three layers, a core (absorptive or non-absorptive) which is inert to the active ingredients, a layer of one or more active ingredients, and a final coating of a semipermeable film former. Depending on the
- 15 application, release of the active ingredients can be adjusted in a targeted manner. The active ingredient(s) can be fixed underneath the film former, and the film former acts as the final layer which governs the release rate of active ingredient per unit time. The active ingredient can be applied to the carrier
- 20 surface together with the film former, this resulting in pores in the film layer which contain active ingredient. In this manner, release of the active ingredient is governed by the proportion of active ingredient in the particular stratum of the coating. A further possibility of constructing granules consists in applying
- 25 active ingredient and film former in layers, analogously to the structure of an onion. This construction allows release rates which vary over time to be set since the concentration gradient first causes the active ingredients to be released from the outer layers. Thus, a higher active ingredient content in a deeper
- 30 layer causes a greater release of active ingredient at a later time of the growth stage. Active ingredients on the surface of the granules lead to an initial effect since these active ingredient components are dissolved first and are available for uptake by the plants.
- 35 The active ingredients and the film formers are preferably applied in fluidized-bed coaters. The movement in the fluidized bed permanently causes a certain degree of abrasion, which acts as micropores in the film former and thus renders coating
- 40 polymers, which are, in principle, impermeable, permeable to the active ingredient molecules. As shown in Example 12, the release rate of the active ingredient can be set in a targeted fashion via the heat supplied during the fluidized-bed coating process.
- 45 The carrier comprising the active ingredient which has been applied is subsequently coated with suitable coating materials. Coating materials which are employed for the controlled release of active ingredient from the coated granules are aqueous polymer dispersions, for example wax dispersions, which comprise - based
- 40 on the aqueous wax dispersion - 5 to 40% by weight of an ethylene copolymer wax consisting of 10 to 25% by weight of an α -olefinically unsaturated mono- or dicarboxylic acid with 3 to 8 C atoms and 90 to 75% by weight of ethylene with an MFI value, measured at 190°C and a load of 2.16 kp, of from 1 to 600,
- 45 preferably 5 to 500, in particular 15 to 300, or an MFI value, measured at 160°C and 325 p, of from 1 to 600, 0.1 to 5% by weight of alkali metal hydroxide, ammonia, an alkanolamine or a

dialkanolamine and mixtures of these, and, as remainder, water to 100%.

- The ethylene copolymers to be used for the wax dispersion
- 5 comprise 10 to 25, preferably 15 to 24, % by weight of α -olefinically unsaturated mono- or dicarboxylic acids with 3 to 8 C atoms, amongst which acrylic acid, methacrylic acid, crotonic acid, maleic acid, fumaric acid and itaconic acid may be mentioned by way of example. Preferred amongst these are
- 10 methacrylic acid and in particular acrylic acid and its mixtures.

The ethylene copolymer waxes are characterized in accordance with the invention by a specific MFI (melt flow index). The MFI indicates the amount of polymer melt in grams which, at a

15 specific temperature, can be squeezed through a nozzle of specific dimensions at a specific expenditure of force (strain). The melt flow indices (MFI units) are determined by standards ASTM D 1238-65 T, ISO R 1133-1696 (E) or DIN 53 735 (1970), all of which are identical with each other.

- 20 The wax dispersions furthermore usually comprise bases, namely, as a rule, 0.1 to 5, preferably 1 to 3, % by weight of alkali metal hydroxide, preferably potassium hydroxide or sodium hydroxide, ammonia, a mono-, di- or trialkanolamine having in
- 25 each case 2 to 18 C-atoms in the hydroxyalkyl radical, preferably 2 to 6 C atoms, or mixtures of the abovementioned alkanolamines or a dialkylmonoalkanolamine having in each case 2 to 8 C atoms in the alkyl and the hydroxyalkyl radicals, or mixtures of these. Examples of amines which may be mentioned are diethanolamine,
- 30 triethanolamine, 2-amino-2-methylpropan-1-ol or dimethylethanolamine. Ammonia is preferably used.

- The base component in the wax dispersions causes at least some of the carboxylic acid groups in the copolymer waxes to be present
- 35 in the salt form. Preferably, 50 to 90, especially 60 to 85, % of these groups are neutralized.

The coating layer may comprise additional substances for controlling the release of the active ingredients. Examples of

40 these are water-soluble substances such as polyethylene glycols, polyvinylpyrrolidone, polyvinylpyrrolidone/polyvinyl acetate copolymers. For example, they amount to 0.1 to 5% by weight, preferably 0.1 to 3% by weight, based on the coating material.

- 45 Coating polymer dispersions which are suitable are combinations of water-insoluble polymers which can be processed as an aqueous or solvent-containing dispersion, such as, for example,

copolymer dispersion of acrylic and methacrylic esters, polyethylene wax emulsions (75-90% ethylene, 10-25% α -olefinically unsaturated mono- or dicarboxylic acid), 50 mol% dimethyl terephthalate + approx. 50 mol% adipic acid + 5 150 mol% 1,4-butanediol, 10-95% polyvinyl acetate + 5-90% N-vinylpyrrolidone-comprising polymer (Kollidon 30, BASF AG), zinc salt of ethylenemethacrylic acid (see Table 1).

- 10 The coating layer is expediently applied by spraying on solutions, dispersions or dispersions [sic] of the abovementioned coating materials in organic solvents or water. An aqueous suspension or an emulsion of the coating material which, in particular, comprises 0.1 to 50, especially 1 to 35, % by weight 15 of polymer material is preferably used. Further auxiliaries for optimizing processability may also be added, for example surfactants, solids such as talc and/or magnesium stearate and/or starch.

20	Coating polymer		Composition	Manufacturer
25	A	Acronal® 290D	butyl acrylate/styrene copolymer	BASF AG
30	B	Acronal® A 603	copolymer dispersion of acrylic and methacrylic esters	BASF AG
	C	Acronal® S 725	butyl acrylate/styrene copolymer	BASF AG
	D	Acronal® S 760	butyl acrylate/styrene copolymer	BASF AG
35	E	Acronal® A 627	copolymer dispersion of acrylic and methacrylic esters	BASF AG
	F	Poligen® WE4	Polyethylene wax emulsion	BASF AG
40	G	Poligen® WE3	polyethylene wax emulsion (75-90% ethylene, 10-25% α -olefinically unsaturated mono- or dicarboxylic acid,	BASF AG
45	H	Polyester	50 mol% dimethyl terephthalate + approx. 50 mol% adipic acid + 150 mol% 1,4-butanediol	BASF AG

0050/49248-020101

I	PVA	10-95% polyvinyl acetate + 5-90% N-vinylpyrrolidone-comprising polymer	BASF AG
J	Surlyn® 9970	zinc ethylenemethacrylate	Exxon

Table 1: polymer dispersions

Especially preferred is a wax dispersion comprising 5 to 40% by weight of an ethylene copolymer wax, 0.1 to 5% by weight of ammonia and 55 to 94.9% by weight of water, or is composed of these components, the ethylene copolymer wax being made of 75 to 90% by weight of ethylene units and 10 to 25% by weight of units of an α -olefinically unsaturated mono- or dicarboxylic acid having 3 to 8 C atoms.

The coating polymers used in accordance with the invention are generally known or can be obtained by known methods (cf., for example, EP 166 235, EP-A 201 702, US-A 5,206,279).

Spraying on is carried out, for example, in fluidized-bed apparatuses or in drums or rotating disks in which the carrier granules are rolled, in perforated vats with controlled drying medium supply, or by air-suspension methods. In general, this is done at temperatures between 10°C and 110°C.

The resulting coated fungicidal compositions can be used as such for the control according to the invention of fungi with controlled release of active ingredient(s).

However, it may also be advantageous externally to apply additional active ingredients to these compositions. The resulting compositions allow further graduation of the controlled release of active ingredient, the active ingredients applied externally to the coating being important for a more directed initial effect. Additionally, it may be advantageous to use a second coating, which provides a further possibility of controlling the delayed release of the active ingredients.

For example, the fungicidal compositions generally comprise between 0.01 and 15, preferably 0.1 to 10, % by weight of crop protection active ingredient.

Depending on the nature of the desired effect, the application rates are between 0.02 and 5 kg, preferably 0.05 and 3 kg, of crop protection active ingredient per ha.

The fungicidal compositions are distinguished by an outstanding activity against a broad spectrum of phytopathogenic fungi, in particular from the classes of the Ascomycetes and Basidiomycetes.

5

They are especially important for controlling a large number of fungi on a variety of crop plants such as cereals, for example wheat, rye, barley, oats, rice, oilseed rape, sugar beet, maize, soybeans, coffee, sugar cane, ornamentals and vegetables such as cucumbers, beans, potatoes and cucurbits. The fungicides prepared in accordance with the invention are especially advantageously used for controlling fungi on cereals.

The compositions are expediently applied in such a way that the composition is allowed to act in the soil, on the seed applied to the soil, or on plants developing therefrom, or on seedlings. Application of the composition and application of the seed, or the planting of the seedlings, may be carried out in separate operations, it being possible to apply the composition before or after the seed, or after planting seedlings.

It is especially advantageous to apply the formulated crop protection active ingredients concomitantly with the seed, or the planting of the seedlings.

25

The examples which follow illustrate the invention.

General method

30 Preparation of controlled-release granules

The granules were prepared in three different laboratory fluidized-bed plants. One of the three fluidized-bed coat-ers is the HKC-0.5/5 TJ by Hüttlin. This is a fluidized bed with a product feed tank A of approx. 5 l and a product feed tank B of approx. 0.5 l. The bottom of the fluidized bed is provided with diagonal slits producing a rotating stream of the fluidizing gas. This leads to uniform mixing of the feed material. The large plant has a diameter of 300 mm and a process chamber height of approximately 800 mm. The fluidized bed has three two-substance nozzles embedded in the bottom. In the small plant by Hüttlin, the container has a diameter of 150 mm and is provided with 2 nozzles. Nozzle diameter: 0.8-1.2 mm (depending on the viscosity of the dispersion feed material), spray pressure: 0.5-1.5 bar. Secondary gas stream: 0.3-1.2 bar. The plant can be operated with air or inert gas. The third fluidized-bed coater is made in-house and has a process chamber diameter of 100 mm. The

height of the process chamber is approx. 600 mm. The plant is provided with a perforated bottom or alternatively with a bottom provided with diagonal slits. The plant can be operated with one nozzle in the bottom and one nozzle in the process chamber. All

- 5 fluidized-bed coaters employed (HKC 5 TJ, HKC 05 TJ and the in-house model) can be operated at axial gas speeds of up to 1.9 m/s and gas temperatures of up to 120°C.

Batches of approx. 200 - 4000 g were produced for the
10 experiments. First, the plant is charged with the feed granules. For example the following feed granules were tested:

- a) water-soluble granules
Rasenflorantid® (Compo, Münster) fertilizer: diameter
15 0.7-2 mm, various fractions
Nitrophos® NP 20/20 (BASF AG, Ludwigshafen) fertilizer:
diameter 2-4 mm, various fractions
prilled urea: prill diameter 0.5-3 mm, various fractions
- 20 b) insoluble granules
sand: 0.3 - 0.8 mm, average size: 0.6 mm
sand: 0.6 - 1.2 mm, average size: 0.85 mm
pumice: approx. 0.4 - 1 mm
limestone: approx. 0.6 - 1.5 mm
- 25 c) biodegradeable absorptive granules
paper pulp granules: diameter 0.3 - 0.9 mm
corn grit: diameter approx. 1.5 - 3 mm
corn straw (corn-cob): diameter 0.5 -1.25 mm, various
30 fractions

The granules are fluidized using the fluidizing gas and is heated to approx. 35-40°C. Then, a suspension or solution which may
comprise 1-6 active ingredients is sprayed on.

35

Spraying on can be done in 3 ways:

1. Active ingredients are sprayed onto the carrier as the first layer, followed by the polymer layer. If appropriate, active
40 ingredient formulations which are not miscible with each other can be sprayed from each of the three nozzles.
2. Active ingredients are mixed with some of the film former, or some of the film former is sprayed within the first 25-50% of
45 the layer with active ingredients from different nozzles, but simultaneously.

33

3. Active ingredients are sprayed simultaneously with the film former from separate nozzles during the entire coating process from separate nozzles.

5 During the spraying process, the amount of gas is set to such a level that the granules are agitated thoroughly.

The following compounds were employed in the examples:

10 Compound 1: Fenpropimorph

(±)-cis-4-[3-(4-tert-butylphenyl)-2-methylpropyl]-2,6-dimethyl-morpholine

15 Compound 2:

1-(4-chlorophenyl)-3-(2-(methoxymethoxycarbonylamino)benzyl)-imidazole

20 Compound 3:

2-[2-(2-isopropoxy-2-(Z)-methoxyimino-1-methyl-(E)-ethylidene-aminooxymethyl)phenyl]-2-(E)-methoxyimino-N-methylacetamide

25 Compound 4:

(E)-2-methoxyimino-2-{2-[(2,5-dimethylphenyl)oxymethyl]phenyl}-N-methylacetamide

30 Compound 5: Bion

5-methyl [sic] benzo[1,2,3]thiadiazole-7-carbothioate

Compound 6: epoxiconazole

35

(2RS,3SR)-1-[3-(2-chlorophenyl)-2,3-epoxy-2-(4-fluorophenyl)-propyl]-1H-1,2,4-triazole

Compound 7: acetylsalicylic acid

40

Compound 8: Juwel® (kresoxim-methyl and epoxiconazole)

(Methyl methoxyimino-α-(o-tolyloxy)-o-tolylacetate and

(2RS,3SR)-1-[3-(2-chlorophenyl)-2,3-epoxy-2-(4-fluorophenyl)-propyl]-1H-1,2,4-triazole

45

Compound 9: Opus® Top

epoxiconazole and fenpropimorph

5 Granule elution apparatus

- The plant serves to determine the delayed release of active ingredients or salts from controlled release (CR) formulations. A frit on which the granules to be tested are placed is located in
- 10 a cylindrical vessel at the lower edge. Underneath the frit there is an S-shaped drain which causes liquid to drain from the cylinder only when it is 80% full. Water (if appropriate together with wetter) is pumped through the CR formulations in a cylindrical feed container (approx. volume 100 ml) by means of a
- 15 hose pump in such a way that the feed material is surrounded completely by water. The percolating water is collected in receiving vessels. An automatic switch causes the receiving vessels to be changed in order to determine the release of active ingredients over time. The receiving vessels are located in a
- 20 heated water bath so that elution generally proceeds under comparable conditions. Unless elution temperatures are specified, a bath temperature of 30°C was set.

- The elution plant operates 24 hours a day in conjunction with the
- 25 program control. One elution takes 24 hours, and during this time approx. 4000 ml of fluid are pumped through the feed material and collected in receiving vessels. The active ingredient content in the eluate is determined by means of HPLC or GC. Whether release is uniform can be checked with reference to the feed material.
- 30 The cumulative value provides a measure for assessing granule permeability.

Example 1 - Comparison example

- 35 Samples prepared in accordance with EP-A 0 734 204 resulted in plant damage for phytotoxic active ingredients such as, for example, Compounds 1, 6 and 5. Most of the abovementioned substances result in damage when used at high concentrations, which is also confirmed by the seed-dressing experiments with
- 40 Compounds 6 and 3 which are shown in Table 2. CR (controlled-release) granules in accordance with formulation 1-5 allow a markedly higher concentration to be fed to the plant over a prolonged period, see Compound 6: 125 g/ha instead of 4 g/ha. However, plant damage is observed even in the case of samples
- 45 which have been prepared in accordance with EP-A 0 734 204

35

Preparation: see Example 2, page 29.

The samples were coated with coating material G as described in the process of EP-A 0 734 204.

5

Emergence failure: 100% loss means no growth after sowing.

Run-out [sic] delay: 100% run-out [sic] delay means no growth after sowing.

10

The results demonstrate clearly that all formulations result in damage to the treated plant.

15

20

25

30

35

40

45

Table 2 - Comparison example

Formulation CR granules No.	Diameter of carrier. [mm]	[g/ha]	[g/ha]	Amount in kg/ha	Coating	Percentage [%]	Thickness of layer [µm]	AI-eluante in % 4000 ml/d		biological results		
								AI 1	AI 2	Emergence failure loss [%]	Damage [%]	Delayed emergence [%]
1	1.19	375 Comp. 1	125 Comp. 6	17	G	5.0	13.6	61	24	86	56	
2	1.05	375 Comp. 1	125 Comp. 6	23	G	7.5	18.0	18	7	39	19	
3	0.75	375 Comp. 1	125 Comp. 6	18	G	3	5.1	63	44	90	75	
4	0.75	375 Comp. 1	125 Comp. 6	20	G	6	10.3	19	6	98	80	
5	3.05	30 Comp. 5		140	G	2.0	18.4	21	-	11-25	10-28	
Seed- dressing experiment	-	4 Comp. 6	-	-	-	-	-	-	-	100	100	100
Seed- dressing experiment	-	50 Comp. 3	-	-	-	-	-	-	-	12-25	6-15	32-70

Target crops: spring barley (Beate), spring wheat (Star, Achill)

Example 2 - Comparison example

Table 3 shows yield and disease scores of product samples which had been prepared and tested on spring wheat in accordance with the description which follows.

- a) The active ingredient epoxiconazole was processed in the form of a suspension concentrate of the following composition:

10

500 g/l of epoxiconazole,

15

30 g/l of a block polymer with polypropylene oxide core of approx. molecular weight 3250 onto which ethylene oxide is grafted up to a molecular weight of approx. 6500, as dispersant (BASF, Germany),

20

20 g/l of a sodium salt of a condensate of phenolsulfonic acid, urea and formaldehyde, as dispersant (BASF, Germany), and

25

water to 1 l. The liquid epoxiconazole preparations used in the examples which follow were obtained by diluting this suspension concentrate with a suitable amount of water.

- b) The active ingredient fenpropimorph was processed as an oil-in-water emulsion of the following composition:

30

200 g/l of fenpropimorph,

35

37 g/l of a p-isononylphenol etherified with 8 ethylene oxide units, as emulsifier (BASF, Germany),

40

87.5 g/l of a 1:1 mixture (by weight) of 2-ethylhexanoic acid and a p-isononylphenol etherified with 7 ethylene oxide units, as emulsifier (BASF, Germany), and

water to 1 l.

Preparation: 3000 g of Rasenflorand were introduced into the fluidized bed as the carrier. The granules were pre-warmed to approx. 35-36°C by a gas stream of 250-280 m³/h which had been heated to 50°C. The active ingredient suspension (450 g) was sprayed onto the carrier via 3 nozzles at a rate of 24 g/min. The

09762044-020103

pressure in the two-substance nozzle was 0.8 bar, and a secondary gas stream was applied to aid atomization, also at 0.8 bar. After the active ingredients had been sprayed on, the coating polymer was applied at a spray rate of 25-30 g/min. When spraying the 5 polymer, the inlet air temperature of the gas stream (280 m³/h) was reduced to 40°C, and the product temperature which was established was 28°C. The polymer was processed as an aqueous dispersion with a solids content of 25%.

- 10 Markedly less disease and an increase in relative yield was observed in the areas treated with the CR granules in comparison with the untreated plot. The initial release rate of the active ingredients in sample 3 was high, which resulted in phytotoxic damage upon plant emergence. Due to the rapid release of active 15 ingredient, the long-term action of this sample was insufficient, so that only a minor effect was discernible in comparison with the untreated sample.

20	Formulation	Carrier	Active ingredient	Application rate [g/ha]	Percentage coating	Erysiphe graminis	Lep-tosp-hae-ria	relative yield	Yield in dt/ha
25						Disease level in %			
		Un-treated	0			16	25	100	62
30	1	Rasen-flora-nid	Comp. 1 Comp. 6	375 125	6%	9	18	104	
35	2	Rasen-flora-nid	Comp. 1 Comp. 6	375 125	6%	9	18	103	
	3	Rasen-flora-nid	Comp. 1 Comp. 6	375 125	3%	10	22	97	
40	4	Rasen-flora-nid	Comp. 1 Comp. 6	375 125	4%	9	17	105	
45		2 spray applications, Comp. 10		1000		6	9	112	

Table 3: Experiments on spring wheat Star

Example 3:

- 5 In a stirred vessel, 200 g of vinyl acetate were emulsified in 800 ml of water. The dispersion was treated with a PVP solution (K 30, 20 g solids). In a Hüttlin Kugel Coater (HKC 5) the coating dispersion was applied to carrier granules.
- 10 The carrier granules employed were 4000 g of fertilizer pellets of average diameter 1.25 mm. The carrier granules were pre-warmed in the HKC 5 to a product temperature of 40°C, and a mixture of a 20% fenpropimorph emulsion (36.7 g of active ingredient) and a 45% epoxiconazole suspension (5.7 g of active ingredient) was
- 15 then sprayed onto the granules.

The polymer dispersion was applied as a coating to the carrier granules coated with the active ingredients epoxiconazole and fenpropimorph.

20

The coating process was carried out under the following conditions:

25	3 nozzles (three-substance nozzles)	0.8 mm
	Weight of carrier granules	4000 g
30	Air	400 m ³ /h
	Inlet air temperature	50°C
	Product temperature	40-42°C
	Outlet air temperature	37.5-40°C
	Type of spraying operation	continuously
35	Spray pressure	1 bar
	Spray rate (for active ingredients and coating polymer)	12 g/min
	Process time	90 min
	Final drying time to product temperature 50°C	15 min

40 Table 4

This gives a uniform smooth coating.

- 45 The release rate of the active ingredients was determined in the above-described elution apparatus. To this end, 30 g of the carrier granules were weighed into a trapped container equipped with a frit. In 24 hours, an amount of 3980 g of water was pumped

through the container and collected. 124 mg of fenpropimorph and 19 mg of epoxiconazole were detected in the collected liquid.

- This product was applied together with cereal seed (winter wheat). On average, approx. 3 fungicidal active ingredient pellets were deposited subterraneously per seed kernel. Epoxiconazole was detected in the growing cereal plants two and six months after application. Two months after sowing, 0.038 mg were detected per kg of biomass, and six months after application 0.022 mg were still detected per kg of biomass.

This demonstrated that the PVA+PVP coating guaranteed a controlled release of the active ingredient epoxiconazole in the soil over at least 6 months.

Example 4

- The active ingredient granules prepared in accordance with the invention are described by way of example in the tables which follow. In Table 5, column 2 indicates the granule carrier, column 3 the mean diameter of the carrier granules in mm. Columns 4-6 contain the active ingredients and their application rate in g/ha, the columns which follow indicate the active ingredient concentrations in the finished granules (according to HPLC/GC analyses). The amount in kg/ha indicates the total amount of granules required to apply the desired amounts of active ingredient per ha.

- The active ingredients were prepared as described in Example 2. The operating conditions of the fluidized-bed plant are described in Table 5 + 6.

Table 5

Formulation	Carrier diameter [mm]	Rate of active ingredient [g/ha]			Active ingredients [actual]			Amount kg/ha
		AI1	AI2	AI3	AI1 %	AI2 %	AI3 %	
1	XAF 1.1	375 g/ha Comp.1	125 g/ha Comp.6	-	1.96	0.69	-	19
2	XAF 1.1	375 g/ha Comp.1	125 g/ha Comp.6	-	1.97	0.65	-	19
3	XAF 1.1	375 g/ha Comp.1	125 g/ha Comp.6	-	2.09	0.78	-	17
4	XAF 1.1	375 g/ha Comp.1	125 g/ha Comp.6	-	1.97	0.65	-	19
5	XBF 3.2	250 g/ha Comp.2	-	-	0.17	-	-	150
6	XBF 3.2	250 g/ha Comp.3	-	-	0.17	-	-	146
7	XBF 3.2	250 g/ha Comp.3	-	-	0.36	-	-	69
8	XBF 3.2	250 g/ha Comp.4	-	-	0.19	-	-	135
9	XBF 3.2	250 g/ha Comp.4	-	-	0.21	-	-	117
10	XBF 3.2	30 g/ha Comp.5	-	-	0.04	-	-	122
11	XBF 3.2	30 g/ha Comp.5	-	-	0.03	-	-	167
12	XBF 3.2	250 g/ha Comp.3	-	30 g/ha Comp. 5	0.15	-	0.04	185
13	XAF 1.3	-	125 g/ha Comp.6	-	0.00	0.44	-	43
14	XAF 1.3	30 g/ha Comp.5	-	-	0.11	-	-	47
15	XKF 1.4	30 g/ha Comp.5	250 g/ha Comp.3	-	0.14	0.48	-	44
16	XKF 1.4	250 g/ha Comp.3	125 g/ha Comp.6	-	0.62	0.43	-	42
17	XKF 1.4	250 g/ha Comp.3	125 g/ha Comp.6	125 g/ha Comp.7	0.58	0.36	0.30	48

For- mula- tion	Car- rier	Car- rier diameter [mm]	Rate of active ingredient [g/ha]			Active ingre- dients [actual]	Amount
18	XNF	0.9	200 g/ha Comp.3	125 g/ha Comp.6	30 g/ha Comp.5	1.85 1.02	12
19	XNF	0.9	200 g/ha Comp.3	125 g/ha Comp.6	30 g/ha Comp.5	1.35 0.8	10

XAF Rasenflorantid®
 XBF Nitrophos® NP 20/20
 XKF Urea
 XOF Limestone
 XNF Sand

101020-41025/60

Table 6 contains the same granules as Table 5. First, the coating is described in greater detail (type, % and thickness). Then, the release of active ingredient in the eluate at 30°C is indicated in %.

5 The columns which follow indicate the operating conditions for spraying the active ingredient and spraying the coating. Polymer composition, see description pages 22 and 23, active ingredient composition page 27. Some samples were after-baked to improve film formation of the coating polymer at the end of the process.

10

15

20

25

30

35

40

45

00762044.020103

Table 6

For- mula- tion No.	Car- rier	Layer		AI eluate, at 4000 ml/24 h				Operating conditions								
								Active ingredient			Coating					
		Coa- ting poly- mer	Per- centa- ge [%]	Thick- ness [μm]	Thick- ness calcu- lated	AI1 [%]	AI2 [%]	AI3 [%]	T [°C]	Spray rate [g/ min]	Gas [g/ min]	T [°C]	t coa- ting [min]	Spray rate [g/ min]	Gas [m³/h]	After ba- king [min]
1	XAF	G	5.4	13	53.4	23.2		40	20	268	30		30	357	0	
2	XAF	I	5.4	13	19.1	8.8		37	26	345	35		21	404	0	
3	XAF	G	3	7	18.0	7.4		36	25	340	35		20	380	0	
4	XAF	G	4	10	19.1	8.8		37	21	345	34		25	370	0	
5	XBF	G	2	18	20.9			40	6	335	38	15	16	345	15	
6	XBF	G	2	18	76.6			40	12	335	38	12	20	335	15	
7	XBF	G	4	37	22.2			40	25	375	38	10	24	395	15	
8	XBF	G	2	18	2.6			40	25	375	38	10	20	395	15	
9	XBF	G	4	37	0.3			40	8	350	38	25	19	370	15	
10	XBF	G	2	18	47.6			39	25	360	40	13	19	380	15	
11	XBF	G	4	37	12.7			40	25	370	38	21	22	390	15	

0050-49248-60

For- mula- tion No.	Car- rier	Layer		AI eluate, at 4000 ml/24 h				Operating conditions									
								Active ingredient			Coating						
		Coa- ting poly- mer	Per- centa- ge [%]	Thick- ness [μm]	AI1 [%]	AI2 [%]	AI3 [%]	T [°C]	Spray rate [g/ min]	Gas [g/ min]	prod [°C]	t [min]	coo- ling [min]	Spray rate [g/ min]	Gas [m³/h]	After ba- king [min]	
12	XBF	G	4	37	56.4			20.0	40		9	400	46	12	20	370	15
13	XBF	G	6	18			6.1		33		6	440	43	23	42	470	30
14	XBF	G	6	18		24.3			32		25	300	39	46	21	360	30
15	XBF	G	6	18		0.0	0.0		30		25	340	42	34	28	340	30
16	XRF	G	6	18		78.9	8.2		38		25	330	44	35	27	380	30
17	XRF	G	6	18		51.4	15.1	61.1	43		12	330	46	36	27	420	30
18	XNF	H	12	36		7.2	1.8	9.0	36		5	45	38	30	5	50	20
19	XNF	G	12	36		1.3	0.7	4.3	37		5	42	41	30	5	50	20

The granules were prepared as described for Example 4.

101020*44029Z60

Example 5

Table 7 gives a variety of coating polymers which were tested for their suitability for controlled-release granules.

Sample preparation:

- 1) Feed 3000 g of carrier material into the fluidized bed,
10 pre-heat to 35°C.
- 2) Spray on a 40% epoxiconazole suspension which, in addition to
active ingredient, also comprises dispersant and wetter.
- 15 Spray conditions: Gas throughput 300 m³/h, product
temperature approx. 33-36°C, spray rate of the active
ingredient suspension 20 ml/min
- 3) Spray polymer from a dispersion, gas throughput 350-380 m³/h,
20 product temperature 35-40°C, spray rate: 20 ml/min

At a gas throughput of 350 m³/h, after-bake the polymer for
15 minutes, product temperature 40°C.

25

30

35

40

45

Table 7 -Comparison of the controlled-release properties of various coating polymers

Formulation (see Example 4)	Carrier diameter [mm]	Carrier diameter content [%]	Active ingredient content [%]	Coating composition	Coating composition	Concentration of polymer dispersion	Fluid phase of dispersion	Percentage [%]	Layer thickness [μm]	Eluted active ingredient m ² granule surface area, g weight and after elution liquid [mg AI/w/ml]
1	XBF	3.05	0.90	Poligen WE 3	G	25%	Water	12.0	36.0	4.4E-7
2	XBF	3.05	1.022	Polyester	H	20%	Water	12.0	36.0	4.3E-6
3	XBF	3.05	0.07	Acronal 290D	A	20%	Water	4.0	35.6	7.0E-6
4	XBF	3.05	0.08	Surlyn 9970	J	2%	boiling THF	1.0	8.9	1.4E-5
5	XBF	3.05	0.49	PVA (Col-I licoat)	I	10%	Water/ 20 % ethanol	5.0	12.0	1.4E-5
6	XBF	3.05	0.07	Acronal S 725	C	20%	Water	4.0	35.6	1.7E-5

Formulation (see Example 4)	Carrier	Carrier diameter [mm]	Active ingredient content[%] epoxico- nazole	Coating	Coating composition	Concentration of polymer dispersion	Fluid phase of dispersion	Percentage [%]	Layer thickness [µm]	Eluted active ingredient m ² granule surface area, g weight and after elution liquid [mg AI/w/ ml]
8	XBF	3.05	0.08	Poligen WE4	F	20%	Water	4.0	35.6	2.2E-5
9	XNF	3.05	0.07	Acronal A 603	B	20%	Water	4.0	35.6	2.3E-5
10	XNF	0.75	0.07	Arconal S 760	D	20%	Water	4.0	35.6	3.5E-5
14	XNF	0.75	0.07	Arconal A 627	E	20%	Water	4.0	35.6	6.5E-5

XBF NP 20/20

XNF sand

Example 6:

The CR granules comprise systemic strobilurins as active ingredients, which, surprisingly, do not suffer from the poor efficacy of the azoles and morpholines (of Table 3). In Tables 8 a and b, 2 CR granule samples with a strobilurin of the oxime ether type and a 2 and 4% coating were tested against two spray applications of a strobilurin + azole Juwel®) in winter barley.

10

For both CR granules (base: Nitrophos® NP 20/20), a duration of action of 8 months and a marked reduction in disease, resulting in a comparable yield as for the spray-treated area, were found. The sample with the thinner coating proved to be less efficient

15 shortly before harvesting, leading to a yield loss of 7% compared with the CR sample with the thicker coating. The fact that comparable biological results can be achieved with a markedly lower rate of active ingredient in comparison with spraying is especially noteworthy.

20

25	Formulation (see Example 4)	Carrier	Active ingredient	Application rate [g/ha]	Coating percentage	Rhynchosporium	Relative yield	Yield dt/ha
						Disease in [%]		
30			Untreated	0		14	100	62.4
35	6	NP 20/20	Comp. 3	250	2 %	6	122	
	7	NP 20/20	Comp. 3	250	4 %	2	129	
40		2 spray treatments with Comp. 8		500		0	132	

Table 8a: Experiments on winter barley Danilo

50

5	Formulation (see Example 4)	Carrier	Active ingre- dient	Appli- cation rate [g/ha]	Coating percen- tage	Pyreno- phora	Rela- tive yield	Yield dt/ha
			Untrea- ted			Disease in [%]		
				0		19	100	72,5
10	6	NP 20/20	Comp. 3	250	2 %	11	116	
	7	NP 20/20	Comp. 3	250	4 %	5	125	
15		2 spray treatments with Comp. 8		500		0	129	

Table 8b: Experiments on winter barley Noveta

20 Example 7

25 Strobilurin efficacy can be improved even further when several
active ingredients are combined with each other, which should be
considered to prevent resistance. Tables 9a and b show a
comparison of scores and yields achieved with a mixture of
various CR granules with the spray treatment. The test material
was granules comprising the same strobilurin type as in Tables
8 a and b in combination with granules comprising a systemic
resistance inductor (Bion®) together with one more active
ingredient.

30

35

40

45

5	Formulation (see Example 4)	Carrier	Active ingre- dient	Appli- cation rate [g/ha]	Coat- ing per- centa- ge	Rhyn- cho- spo- rium	Puccinia	Rela- tive yield	dt/ ha
			Un- trea- ted	0		Disease in [%]			
10	8	NP 20/20	Comp. 4	250	2 %	3	1	146	
6			Comp. 3	250					
10			Comp. 5	30					
15									
20		2 spray ap- plica- tions	Comp. 8	500		0	0	149	

Table 9a: Experiments on winter barley Danilo

25	Formulation (see Example 4)	Carrier	Active ingredient	Application rate [g/ha]	Coating percentage	Pyrenophora	Relative yield	Yield dt/ha
			Un-treated			Disease in [%]		
30			0			22	100	61.7
8		NP 20/20	Comp. 4	250	2 %	5	128	
6			Comp. 3	250				
10			Comp. 5	30				
40		2 spray applications	Comp. 8	500		1	125	

45 Table 9b: Experiments on winter barley Noveta

Example 8

In Table 10, the CR granule formulations of Table 8 are tested in winter wheat. In addition to the CR granules comprising one active ingredient and the mixture of granules comprising various active ingredients (Table 9), this table additionally contains a formulation comprising two active ingredients on one type of granules.

10	Formulation (see Example 4)	Carrier	Active ingredient	Application rate [g/ha]	Coating percentage	Erysiphe graminis	Leptosphaeria	Relative yield	Yield dt/ha
15			Untreated	0		Disease in [%]			
						11	63	100	53.3
20	6	NP 20/20	Comp. 3	250	2 %	5	40	108	
	7	NP 20/20	Comp. 3	250	4 %	4	31	120	
25	12	NP 20/20	Comp. 3	250	4 %	2	24	132	
			Comp. 5	30					
30		2 spray applications	Comp. 8	500		0	2	140	

Table 10: Experiments on winter barley Frühgold

In winter wheat, which has a longer growing period, it emerges that the sample with the thicker coating gives better biological results; surprisingly, the sample comprising two active ingredients shows a synergistic effect which exceeds that of the mixture of the individual active ingredient granules of Table 9.

40 Example 9

Again, the synergistic effect in winter wheat is shown clearly in Table 11. In this case, CR granules comprising various active ingredients were mixed (2 or 3 single-ingredient granules).

53

The product comprising the readymix on one type of granules was much more effective than the granule mixture (see formulations No. 7, No. 9, No. 11 and No. 12, Example 4).

5	Formulation (see Exam- ple 4)	Car- rier	Active ingre- dient	Appli- cation rate [g/ha]	Coa- ting per- centa- ge	Erys- phe grami- nis	Lepto- sphae- ria	Rela- tive yield	Yield dt/ha
10			Un- trea- ted	0		11	32	100	62.3
15	7	NP 20/20	Comp. 4	250	4 %	8	18	112	
	9		Comp. 3	250					
20	7	NP 20/20	Comp. 4	250	4 %	3	9	114	
	9		Comp. 3	250					
	11		Comp. 5	30					
25	12	NP 20/20	Comp. 3	250	4 %	4	12	121	
			Comp. 5	30					
30		2 spray appli- ca- tions	Comp. 8	500		0	3	126	

Table 11: Experiments on winter wheat Kanzler

Example 10

35 Table 12 shows these super-synergistic effects which are achieved with more than one active ingredient on one type of granules in comparison with granule mixtures, this time on spring wheat. The carriers employed were urea and Rasenflorand granules.

40

45

	Formulation (see Example 4)	Car- rier	Active ingre- dient	Appli- cation rate g/ha	Coating percen- tage	Disease in %	
						Erysiphe graminis	Lepto- sphae- ria
5			Untrea- ted	0		9	11
	15	Urea	Comp. 3	250	6 %	0	1
			Comp. 5	30			
10	16	Urea	Comp. 3	250	6 %	1	1
			Comp. 6	125			
	17	Urea	Comp. 3	250	6 %	0	1
15			Comp. 6	125			
			Comp. 7	125			
	13	Rasen- flora- nid	Comp. 6	187	6 %	3	2
20	14		Comp. 5	30			
		2 spray ap- plica- tions	Comp. 8	500		0	0
25							

Table 12: Experiments on spring wheat Star

Two experimental combinations are noteworthy in this table.

Epoxiconazole (Comp. 6.) alone suffered from substantial shortcomings (see Table 3). In combination (granules 2) with the plant activator Bion® (Comp. 5), the effect of epoxiconazole is markedly better. Surprisingly, acetylsalicylic acid (Compound 7) is found to show the same activity-enhancing effects as Bion® (Compound 5) in this experimental series.

Example 11

Table 13 shows the effect of a filler in the coating polymer on the release rate. For example, if the cold-water-soluble starch C-Pur® by Ceresta is employed as filler of the coating polymer, the release rate increases markedly with increasing amounts of filler.

Active ingredient	Coating percentage	Filler	Release rate in 24 h at 40°C, 4000 ml
Epoxiconazole	4 %	0 %	2.70 %
Epoxiconazole	4 %	10 %	3.30 %
Epoxiconazole	4 %	20 %	7.15 %

Table 13

The granules were prepared by the method described in Example 4.

Batch size: 600 g, inlet air temperature: 45°C, product temperature: 39°C, gas flow rate: 1.8 m/sec

Example 12

Table 14 shows how the release rate is affected by the operation of the fluidized-bed drying process. The heat input, in particular, has a marked effect on the leaching properties. The more heat energy is supplied with otherwise constant conditions, the lower the release rate with polymer layers of equal thickness. Doubling of the energy supplied results in a reduction in microporosity of the polymer film to approx. 1/10, which is demonstrated by the release rate.

Table 14a

Sam- ple	Carrier	Active ingre- dient [%] Comp. 6	Active ingre- dient [%] Comp. 3	% coa- ting Poligen WE3	Gas flow rate [m/s]	Inlet air tempe- rature [°C]	Product temp- erature [°C]	Outlet gas tempe- rature [°C]	Spray- ing time [min]	Spray- ing rate [g/min]	After- baking time [min]
1	NP 20/20	0.091	0.16	4	1.84	45.7	40.7	37.2	24	26	15
2	NP 20/20	0.076		4	1.73	45.2	40.5	37.5	24	25	10
3	NP 20/20	0.083		4	1.53	49	40	38	13	27.5	10
4	NP 20/20	0.075		4	1.61	27	23	23	16	30	20
5	urea	0.394	0.80	9	1.47	49.3	39.8	37.2	45	24	10

Fluidized-bed plant, container diameter 300 mm, batchwise operation, batch size: 3-4 kg,

Carrier diameter 3-4 mm, mean layer thickness: 37.5 μ m

Samples 1-4: D = 3-4 mm; mean layer thickness approx. 37.5 μ m

Sample 5: D = 1.3-2 mm; mean layer thickness approx. 27.5 μ m

Table 14 b - Samples of Table 14a: leaching rate and heat input

5	Sample	Leaching rate [% of initial quantity in 4000 ml per 24 h at 30°C]		Heat input [kJ/kg]	Heat input [kJ/kg polymer]
		Comp. 6	Comp. 3		
	1	2.1	4.9	653	16,322
10	2	9.8		517	12,927
	3	14.9		475	11,864
	4	19.1		331	8282
	5	3.2	8.02	1400	15,139

15 The heat input (in kJ/kg) is calculated from the following data:

$Q = \Delta T * V * t * C_p / m$ $Q_{pol} = \Delta T * V * t * C_p / m_{polymer}$
 $\Delta T =$ Inlet air temp. minus outlet gas temp. (gas temperature at inlet port minus gas temperature at outlet port)
 20 $V =$ Gas volume flow, calculated from gas flow rate
 $C_p =$ Gas constant
 $t =$ Total sample residence time (spraying time of the coating polymer + after-baking time)
 $m =$ Batch size in kg
 25 $m_{polymer} =$ Amount of polymer in the batch

30

35

40

45

Table 14c - Long-term experiment in the open

Granule samples 1 and 5 of Table 14a + b were buried in soil.

- 5 After 6 months, the samples were analyzed for their residual active ingredient,

10	Sample	Leaching rate [% of the originally employed amount after 6 months]	
		Comp. 6	Comp. 3
	1	12	17
	5	35	45

15

20

25

30

35


40

45

00702044-00000000

We claim:

1. Soil-applied CR granules obtainable by applying an
5 active-ingredient-comprising coating to a solid carrier in a fluidized bed with a defined heat input adjustable to 6000 to 25,000 KJ/KG [sic] of coating polymer.
2. Soil-applied CR granules as claimed in claim 1 with an
10 active-ingredient-comprising coating of
 - 0.1-25% by weight of one or more active ingredients
 - 1-40% by weight of one or more coating polymers
 - 0-60% by weight of one or more additives,
- 15 the total of the % by weight of the compounds in the coating being 100% by weight.
3. Soil-applied CR granules as claimed in claim 2 comprising, as
20 coating polymer, a dispersion from amongst the following groups: butyl acrylate/styrene copolymers, copolymer dispersions of acrylic and methacrylic esters, polyethylene wax emulsions, polyesters composed of the following units:
 - 50 mol% dimethyl terephthalate + approx. 50 mol% adipic acid
 - 25 + 150 mol% 1,4-butanediol + trace elements, mixture of 10-95% polyvinyl acetate + 5-90% n-vinylpyrrolidone-comprising [sic] polymers, ethylene/methacrylic acid zinc salt.
4. Soil-applied CR granules as claimed in claim 3 comprising, as
30 coating polymer, at least one from amongst the group of the biodegradable polyesters.
5. Soil-applied CR granules as claimed in claim 1 comprising, as
35 active ingredient, at least one fungicidal compound of the formula I from amongst the class of the strobilurins.



in which the substituents have the following meanings:

A is NOCH₃, CHOCH₃, CHCH₃;

- Y is O, NH;
- T is oxygen or oxymethylene;
- 5 Z is a group X, $N=C(R^1)W$ or $N=C(R^1)-C(R^2)=NOR^3$;
- X is unsubstituted or substituted heterocyclyl, unsubstituted or substituted aryl, unsubstituted or substituted hetaryl;
- 10 W is unsubstituted or substituted alkyl, unsubstituted or substituted alkenyl, unsubstituted or substituted alkynyl, unsubstituted or substituted cycloalkyl, unsubstituted or substituted cycloalkenyl, unsubstituted or substituted heterocyclyl, unsubstituted or substituted aryl or unsubstituted or substituted hetaryl;
- 15 R^1 is hydrogen, cyano, C_1-C_4 -alkyl, C_1-C_4 -haloalkyl, C_1-C_4 -alkoxy, C_1-C_4 -alkoxy- C_1-C_4 -alkyl, C_3-C_6 -cycloalkyl;
- 20 R^2 is hydrogen, cyano, halogen, $C(R^d)=NOR^3$ or W, OW, SW or NR^cW , where
- R^c is hydrogen, alkyl, alkenyl or alkynyl;
- 25 R^d is hydrogen or alkyl;
- R^3 is hydrogen, unsubstituted or substituted alkyl, unsubstituted or substituted alkenyl or unsubstituted or substituted alkynyl,
- 30 or a salt thereof.
6. Soil-applied CR granules as claimed in any one of claims 1-5, comprising an active ingredient from the group of the systemically acting strobilurins, the azoles or the salicylates.
- 35 7. Soil-applied CR granules as claimed in any of claims 1-5, comprising, as active ingredient, 5-methyl [sic] benzo[1,2,3]thiadiazole-7-carbothioate.
- 40 8. Soil-applied CR granules as claimed in claim 1, comprising, as carrier, water-soluble, water-insoluble or biodegradable granules.
- 45

61

9. A process for the preparation of soil-applied CR granules as claimed in any one of claims 1-8, which comprises applying, to a carrier, first the active ingredient and then the coating comprising at least one coating polymer and, if appropriate additives in a fluidized bed, micropores being generated in the coating by abrasion or by the directed addition of water-soluble additives (lime, starch).
10. A method for controlling phytopathogenic fungi, undesired vegetation, undesired attack by insects and/or for regulating the growth of plants, which comprises allowing Soil-applied CR granules as claimed in any one of claims 1 to 9 to act on plants, their environment or on seed.
11. The use of the soil-applied CR granules as claimed in any one of claims 1-8 or obtained as claimed in claims 9 and 10 for controlling phytopathogenic fungi, undesired vegetation, undesired attack by insects and/or for regulating the growth of plants.

0972044-000104

Soil-applied granules with controlled release of active ingredient(s) (soil-applied CR granules)

5 Abstract

The present invention relates to soil-applied CR granules obtainable by applying an active-ingredient-comprising coating to a solid carrier in a fluidized bed, to a process for the
10 preparation of these soil-applied granules, and to a method for controlling phytopathogenic fungi, undesired vegetation, undesired attack by insects and/or for regulating the growth of plants using the soil-applied CR granules according to the
15 invention.

20

25

30

35

40

45

Declaration, Power of Attorney

Page 1 of 4

0050/049248

We (I), the undersigned inventor(s), hereby declare(s) that:

My residence, post office address and citizenship are as stated below next to my name,

We (I) believe that we are (I am) the original, first, and joint (sole) inventor(s) of the subject matter which is claimed and for which a patent is sought on the invention entitled

Soil-applied granules with controlled release of active ingredient(s)
(soil-applied CR granules)

the specification of which

☒ is attached hereto.

☐ was filed on _____ as

Application Serial No. _____

and amended on _____.

☒ was filed as PCT international application

Number PCT/EP99/05407

on July 28, 1999

and was amended under PCT Article 19

on _____ (if applicable).

We (I) hereby state that we (I) have reviewed and understand the contents of the above-identified specification, including the claims, as amended by any amendment referred to above.

We (I) acknowledge the duty to disclose information known to be material to the patentability of this application as defined in Section 1.56 of Title 37 Code of Federal Regulations.

We (I) hereby claim foreign priority benefits under 35 U.S.C. § 119(a)-(d) or § 365(b) of any foreign application(s) for patent or inventor's certificate, or § 365(a) of any PCT International application which designated at least one country other than the United States, listed below and have also identified below, by checking the box, any foreign application for patent or inventor's certificate, or PCT International application having a filing date before that of the application on which priority is claimed. Prior Foreign Application(s)

Application No.	Country	Day/Month/Year	Priority Claimed
19835218.2	Germany	05 August 1998	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No
19846893.8	Germany	13 October 1998	<input checked="" type="checkbox"/> Yes <input type="checkbox"/> No

We (I) hereby claim the benefit under Title 35, United States Codes, § 119(e) of any United States provisional application(s) listed below.

(Application Number)

(Filing Date)

(Application Number)

(Filing Date)


We (I) hereby claim the benefit under 35 U.S.C. § 120 of any United States application(s), or § 365(c) of any PCT International application designating the United States, listed below and, insofar as the subject matter of each of the claims of this application is not disclosed in the prior United States or PCT International application in the manner provided by the first paragraph of 35 U.S.C. § 112, I acknowledge the duty to disclose information which is material to patentability as defined in 37 CFR § 1.56 which became available between the filing date of the prior application and the national or PCT International filing date of this application.

Application Serial No.	Filing Date	Status (pending, patented, abandoned)
_____	_____	_____
_____	_____	_____
_____	_____	_____
_____	_____	_____

And we (I) hereby appoint **Messrs. HERBERT B. KEIL**, Registration Number 18,967; and **RUSSEL E. WEINKAUF**, Registration Number 18,495; the address of both being Messrs. Keil & Weinkauff, 1101 Connecticut Ave., N.W., Washington, D.C. 20036 (telephone 202-659-0100), our attorneys, with full power of substitution and revocation, to prosecute this application, to make alterations and amendments therein, to sign the drawings, to receive the patent, and to transact all business in the Patent Office connected therewith.

We (I) declare that all statements made herein of our (my) own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issuing thereon.

1-00
Reinhold Stadler
NAME OF INVENTOR



Signature of Inventor

Date August 12, 1999

Gartenstr.18
67489 Kirrweiler
Germany
Citizen of: Germany
Post Office Address: same as residence

DEX

2-00
Reiner Kober
NAME OF INVENTOR



Signature of Inventor

Date August 12, 1999

Im Schlittweg 20
67136 Fußgönheim
Germany
Citizen of: Germany
Post Office Address: same as residence

DEX

3-00
Karl-Heinrich Schneider
NAME OF INVENTOR



Signature of Inventor

Date August 12, 1999

Am Kelleracker 20
67271 Kleinkarlbach
Germany
Citizen of: Germany
Post Office Address: same as residence

DEX

4-00
Reinhold Saur
NAME OF INVENTOR


Signature of Inventor

Date August 12, 1999

Königsberger Str.9
67459 Röhl-Iggelheim
Germany
Citizen of: Germany
Post Office Address: same as residence

DEX

5-00
Herbert Bayer
NAME OF INVENTOR

Herbert Bayer
Signature of Inventor

Date August 12, 1999

D 3.4
68159 Mannheim
Germany DEX
Citizen of: Germany
Post Office Address: same as residence

6-00
Karl Kolter
NAME OF INVENTOR

Karl Kolter
Signature of Inventor

Date August 12, 1999

Sudentenstr.1
67117 Limburgerhof
Germany DEX
Citizen of: Germany
Post Office Address: same as residence

4-00
Michael Seufert
NAME OF INVENTOR

Michael Seufert
Signature of Inventor

Date August 12, 1999

Wellsring 32
67098 Bad Dürkheim
Germany DEX
Citizen of: Germany
Post Office Address: same as residence